

Test Report

Revision 2

Report Number:
994495-1-TEX rev. 2



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 7
Init.: CHF/LELN
Order no.: 994495
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltoft

Material: Samples of upholstery fabric designated: Vanir. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 2 September 2021.

Period: The test took place from 3 September 2021 to 28 September 2021.

Method: The test methods used are referenced in connection with the results. See page 7.

Test results: The results are shown on page 7.

Remarks: The name has been changed from Fishbone to Vanir according to the customer
This report replaces Report no. 994495-1 rev 1 of 7 february. Wrong number on sample 190 is changed to 193

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant



DIGITALLY SIGNED DOCUMENT

18 February 2022

DANISH TECHNOLOGICAL INSTITUTE








DANAK

TEST Reg.no. 2



Samples

Sample mark	Description	Photo
113	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
133	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
193	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
243	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
293	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	








Samples (*continued*)

Sample mark	Description	Photo
363	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
373	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
393	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
413	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
443	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	



Samples (*continued*)

Sample mark	Description	Photo
473	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
513	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
553	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
573	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
593	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	







Samples (*continued*)

Sample mark	Description	Photo
683	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
693	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
733	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
773	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
813	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	



Samples (*continued*)

Sample mark	Description	Photo
883	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
913	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
983	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	
943	Sample of upholstery fabric Designated: Vanir Fibre content: 92% new wool, 8% nylon	



Results

Test of Samples of upholstery fabric designated: Vanir

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
113	7
133	7
193	7
243	7
293	7
363	6
373	7
393	6-7
413	6-7
443	6-7
473	6-7
513	6
553	6
573	6
593	6
683	6-7
693	6-7
733	6-7
773	6-7
813	6
883	6-7
913	6-7
983	6
943	6
