



**Febrik bv
Minosstraat 20
5048 CK TILBURG
Netherlands**

Your notice of
26-04-2022

Your reference

Date
04-05-2022

Analysis Report 22.02323.03


Required tests :
ISO 12947-2 (2016)

Determination of the abrasion resistance - Martindale

| Sample id | Information given by the client | Date of receipt |
|-----------|---------------------------------|-----------------|
| T2208483 | ARDA 671 | 26-04-2022 |

Lies Alboort
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2208483 - ARDA 671

Determination of the abrasion resistance - Martindale

Date of ending the test 03-05-2022
 Standard used ISO 12947-2 (2016)

Deviation from the standard -
 Conditioning 20°C, relative humidity 65%
 Apparatus Martindale Wear and Abrasion Tester
 Pressure on test specimen 12 kPa
 Abradant Standard wool fabric
 Type of the felt Woven felt
 Approximate g/m² > 500
 Number of test specimens 3

Test end point Knitted - 1 loop completely damaged

| Specimen | Number of rubs | Final result |
|---------------|----------------|--------------|
| #1 | 60 000 | 50 000 |
| #2 | 100 000 | 90 000 |
| #3 | 100 000 | ≥ 100 000 |
| Minimum value | 60 000 | 50 000 |