



Feabrik bv
Minosstraat 20
5048 CK TILBURG
Netherlands

Your notice of
15-03-2022

Your reference

Date
30-03-2022

Analysis Report 22.01459.02

Required tests :

DIN 4102-1B2 (1998)

Burning behaviour - B2

Sample id	Information given by the client	Date of receipt
T2205138	ARDA	15-03-2022

Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Reference: T2205138 - ARDA

Burning behaviour - B2

Date of ending the test 30-03-2022
Standard used DIN 4102-1B2 (1998)

Deviation from the standard -

Conditioning 23°C, relative humidity 50%
Information given by the client Front ≠ back

Ignition Surface

Length front

	1	2	3	4	5
Time to reach 150 mm mark (s) °	*	*	*	*	*
Ignition filter paper within 20 s after flame application	no	no	no	no	no

° tip of the flame
* = time to reach the mark > 20 s or mark not reached

Width front

	1	2	3	4	5
Time to reach 150 mm mark (s) °	*	*	*	*	*
Ignition filter paper within 20 s after flame application	no	no	no	no	no

° tip of the flame
* = time to reach the mark > 20 s or mark not reached

Criteria
- time to reach the mark > 20 s for all test specimens

Conclusion B2