



Feabrik bv
Minosstraat 20
5048 CK TILBURG
Netherlands

Your notice of
04-03-2022

Your reference

Date
08-03-2022

Analysis Report 22.01255.01

Required tests :

IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8	Fire tests - Test for upholstered furniture - smouldering cigarette test
IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8	Fire tests - Test for upholstered furniture - Match flame equivalent

Sample id	Information given by the client	Date of receipt
T2204405	ARDA	04-03-2022

Petra Wittevrongel
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2204405 - ARDA

IMO upholstered furniture

Information given by the client

Type of furniture Seat / sofa / office chair

Fabric

Composition	71% new wool / 8% PA // 21% polyester
Structure	Knitted
Yarn count - warp	Front: nm 28/1
Yarn count - weft	Back: PES 167 dtex
Thickness in mm	3
Weight g/m ²	570
Colour	Green - 991
Fire retardant treatment	No

Reference: T2204405 - ARDA

Fire tests - Test for upholstered furniture - smouldering cigarette test

Date of ending the test	08-03-2022
Standard used	IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8
Deviation from the standard	-
Conditioning	23°C, relative humidity 50%
Filling	T 23140 (Recticel) * - non-fire retardant foam - $\pm 22 \text{ kg/m}^3$ * standard non-FR PU-foam (as indicated in Appendix 2 and 3 of Part 8)
Dimension of the specimens	800 mm x 650 mm x 2 mm
Weight (g/m^2)	613

Ignition source: smouldering cigarette with the following specifications

Length: $(70 \pm 4) \text{ mm}$

Diameter: $(8.0 \pm 0.5) \text{ mm}$

Mass: $(0.95 \pm 0.15) \text{ g}$

Smouldering rate: $(11.0 \pm 4.0) \text{ min} / 50 \text{ mm}$



	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Smoulders more than 1 hour	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Occurrence of flames	no	no
Additional observations		
Maximum extent of damage from the ignition source (mm)	5	5
	non-ignition	non-ignition

Conclusion Pass

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Reference: T2204405 - ARDA

Fire tests - Test for upholstered furniture - Match flame equivalent

Date of ending the test	08-03-2022
Standard used	IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8
Deviation from the standard	-
Conditioning	23°C, relative humidity 50%
Filling	T 23140 (Recticel) * - non-fire retardant foam - ± 22 kg/m ³ * standard non-FR PU-foam (as indicated in Appendix 2 and 3 of Part 8)
Dimension of the specimens	800 mm x 650 mm x 2 mm
Weight (g/m ²)	613
Flame application time (s)	20



	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke/heat/glowing more than 120 s	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Flaming > 120 s	no	no
Afterflame time (s)	0	0
Additional observations		
Afterglow time (s)	0	0
Maximum extent of damage from the ignition source (mm)	35	40
	non-ignition	non-ignition

Conclusion Pass

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.