



Kvadrat A/S
Lundbergsvej 10
8400 Ebeltøft
Denmark

Your Reference
Customer Number 50136
Contact Person Henriksen Lone
E-Mail lh@kvadrat.dk

Vienna / 09.11.2022 / guse

Test Report VN736 210312.1

Application

Testing and classification of the burning behaviour according EN 13773.

Test Material

Shutter

The test material used for testing was made anonymous for laboratory purposes.
A detailed sample list is included in the document.

Issuing

Original Issuing, 09.11.2022
Number Of Included Pages: 9

OETI - Institut fuer Oekologie, Technik und Innovation GmbH

A handwritten signature in blue ink, appearing to read 'Günther Sereinig'.

Günther Sereinig

Customer Service Officer



1 Application

Date of Order	Scope of Order
05.10.2022	Description Of Specimen - Textile Fabrics - DIN 60000 Washing Procedure For Textile Testing - EN ISO 6330 (OZW12) Ignitability Vertical Orientated Specimen - EN 1101 Flame Spread of Vertical Oriented Specimen - supplied cond. - EN 13772 Flame Spread of Vertical Oriented Specimen - after cleaning - EN 13772 Dropping Behaviour - supplied condition - EN 13772 Dropping Behaviour - after cleaning - EN 13772 Classification Of Burning Behaviour Of Curtains And Drapes - EN 13773

2 Samples

No.	Receipt	Sample Identification
1	10.10.2022	Shutter

(Unless otherwise stated samples are provided by the customer.)

3 Tests Performed / Results

*Description Of Specimen - Textile Fabrics DIN 60000

Tested sample: **#1 Shutter**

Type of fibre:	100% polyester FR (declaration by the applicant)
Technological description:	woven fabric

According to the current version of the relevant European Directives, fibre materials with a mass percentage of < 2 % are not specified.



Washing Procedure For Textile Testing EN ISO 6330 (OZW12)

Tested sample: **#1 Shutter**

Standard washing machine	Wascator FOM 71 MP-LAB
Washing procedure	3N - normal wash
Temperature [°C]	30
Total mass of the specimen	1'000 g
Load	2 kg
Loading fabric	knitted 100% polyester fabric textured yarn
Washing detergent	ECE 2 washing detergent
Water hardness	3° dH
Number of washing processes	12
Drying procedure	Method B - Line drying from the dripping wet state

Ignitability Vertical Orientated Specimen EN 1101

 Tested sample: **#1 Shutter**

Test climate:

- Temperature [°C]: 23

- rel. Humidity: [%]: 31

Specimen size [mm]: 200 x 80mm

Test gas: Propan

Mode of ignition: Edge flaming

Pretreatment: None, test was carried out in supplied condition

Longitudinal direction			Cross direction		
Ignition time	Number of		Ignition time	Number of	
	Ignitions	No ignitions		Ignitions	No ignitions
1 s	0	1	1 s	0	1
2 s	0	1	2 s	0	1
3 s	0	1	3 s	0	1
4 s	0	1	4 s	0	1
5 s	0	1	5 s	0	1
10 s	0	1	10 s	0	1
15 s	0	1	15 s	0	1
20 s	0	5	20 s	0	5

Middle ignition time [s]	>20	Middle ignition time [s]	>20
--------------------------	-----	--------------------------	-----

Minimum ignition time [s]	>20
----------------------------------	---------------

Flame Spread of Vertical Oriented Specimen - supplied cond. EN 13772

Tested sample: **#1 Shutter**
 Conditioning climate: 20±2 °C/ 65± 5 % relative humidity
 Test gas: Propan
 Pretreatment: None, test was carried out in supplied condition

Sample	exposed surface	1st marker thread severed	3rd marker thread severed	Time from start of inflammation to burning through of the		destroyed length	flaming debris
				1st marker thread	3rd marker thread		
				[s]	[s]		
Longitudinal direction							
1	right	no	no	--	--	13.0	no
2	left	no	no	--	--	11.0	no
3	right	no	no	--	--	12.0	no
4	right	no	no	--	--	14.0	no
Cross direction							
1	right	no	no	--	--	11.0	no
2	left	no	no	--	--	9.0	no
3	right	no	no	--	--	12.0	no
4	right	no	no	--	--	10.0	no

Precision: With an interlaboratory test with 16 textile samples in 11 European laboratories it showed up that the determined results are reproducible and repeatable. Between all laboratories agreeing results showed up. The uncertainty of the measurement [u] corresponds therefore to the dispersion of the individual values of the respective examination.

Flame Spread of Vertical Oriented Specimen - after cleaning EN 13772

Tested sample: **#1 Shutter**
 Conditioning climate: 20±2 °C/ 65± 5 % relative humidity
 Test gas: Propan
 Pretreatment: 12 washing cycles (see washing procedure)

Sample	exposed surface	1st marker thread severed	3rd marker thread severed	Time from start of inflammation to burning through of the		destroyed length [cm]	flaming debris
				1st marker thread	3rd marker thread		
				[s]	[s]		
Longitudinal direction							
1	right	no	no	--	--	12.0	no
2	left	no	no	--	--	10.0	no
3	right	no	no	--	--	13.0	no
4	right	no	no	--	--	11.0	no
Cross direction							
1	right	no	no	--	--	11.0	no
2	left	no	no	--	--	9.0	no
3	right	no	no	--	--	13.0	no
4	right	no	no	--	--	11.0	no

Precision: With an interlaboratory test with 16 textile samples in 11 European laboratories it showed up that the determined results are reproducible and repeatable. Between all laboratories agreeing results showed up. The uncertainty of the measurement [u] corresponds therefore to the dispersion of the individual values of the respective examination.

Dropping Behaviour - supplied condition EN 13772

 Tested sample: **#1 Shutter**

Pretreatment: none

Comment: The determination of dropping behaviour for curtains classified as Class 1 or 2 is done according to EN 13772.

Longitudinal direction			Cross direction		
Sample	Number of drops	Igniting dropping	Sample	Number of drops	Igniting dropping
1	0	no	1	0	no
2	0	no	2	0	no
3	0	no	3	0	no
4	0	no	4	0	no

Dropping Behaviour - after cleaning EN 13772

 Tested sample: **#1 Shutter**

Pretreatment: 12 washing cycles (see washing procedure)

Comment: The determination of dropping behaviour for curtains classified as Class 1 or 2 is done according to EN 13772.

Longitudinal direction			Cross direction		
Sample	Number of drops	Igniting dropping	Sample	Number of drops	Igniting dropping
1	0	no	1	0	no
2	0	no	2	0	no
3	0	no	3	0	no
4	0	no	4	0	no

***Classification Of Burning Behaviour Of Curtains And Drapes EN 13773**

Tested sample: **#1 Shutter**

Determination of the ignitability according to EN 1101		no ignition
Determination of the flame spread of vertical orientated specimen according to EN 13772 - supplied condition	1st Markerthread	no break
	3rd Markerthread	no break
	Flaming debris	none
Determination of the flame spread of vertical orientated specimen according to EN 13772 - after cleaning	1st Markerthread	no break
	3rd Markerthread	no break
	Flaming debris	none
max. number of drops fall down during EN 13772 test		0
Drops caused ignition of filter paper		none

Classification of burning behaviour

According to the classification criteria of EN 13773 the tested specimen can be classified as:

class 1

Classification of dropping behaviour

The tested specimen can be classified as

not dropping

Not dropping behaviour corresponds in accordance with the former standard ÖNORM B 3800 part 1 point 6.1 to the drop class "Tr1- nicht tropfend"

4 Remarks

Period of Validity

There are no regulations concerning duration of validity in the individual test standards. As the results of the examinations refer only to the submitted and examined samples, the report is valid for these for an unlimited period. A period of validity specified as part of an expert evaluation is in the discretion of the consultant or OETI. The applicability of results and expert evaluations for materials not tested is in the responsibility of the applicant. Whereby an apportionment of results as well as any specified period of validity can only be done for identically constructed products and only as long as the product is produced unchanged. Possible national or international restrictions concerning the terms of usability of test and classification reports have to be considered; this is not the responsibility of the test laboratory.

Sample Material

Results of performed tests only refer to the sample material provided. Without explicit written other agreement testing is destructive and the sample material is transferred to the property of OETI, which is entitled to freely decide on storage and disposal.

Issuing

This test report is only issued as a PDF. Translations will be marked accordingly on the cover sheet.

Quality Management, Accreditation And Notification

All tests and services are performed under a quality management system according to EN ISO/IEC 17025. OETI is accredited as Testing Laboratory and Certification Body for products. It also is a Notified Body (NB0534). (see <http://ec.europa.eu/enterprise/newapproach/nando/>). Accreditation was provided by Akkreditierung Austria. The scope of accreditation is listed on www.oeti.biz. Due to the system for the mutual recognition of national accreditations (ILAC/IAF), this accreditation is valid worldwide.

Statements of conformity are based on the specifications of the specified standard. The "simple acceptance rule" applies, that means the measurement uncertainty is stated for the statement of conformity, but not taken into account.

In this report individual non-accredited test procedures are marked with *. Nevertheless, the analysis was also carried out for these parameters at the same level of quality as for the accredited parameters.

According to the decree on the use of the accreditation mark ("AkkZV") the accredited Conformity Assessment Body is the only one to use the accreditation mark. Application of the registration number of the Notified Body: As to personal protective equipment (PPE) the requirements of Regulation (EU) 2016/425 have to be kept. With construction products the application is only permitted within the declaration of performance for CE-marking.

Copyright And Usage Notes

It is pointed out, that any alterations, amendments or falsifications of reports not authorized by the issuer of the report will be prosecuted as civil and criminal offences; this especially to the appropriate requirements of ABGB, UrhG, UWG and criminal law and their respective international equivalents. Reports are protected under international copyright laws. Written consent of the OETI GmbH is required for publications (also in excerpt) and reference to tests for public relation purposes. Reports may only be reproduced in full length.

End of Report