

Investigation report

SAHCO GmbH
Kreuzburger Str. 17-19
DE 90471 Nürnberg

contact	Detlef v. Seyfried
department	Laboratory\Laboratory manager
phone	+49 (0) 521 / 543 - 498
fax	+49 (0) 521/ 543 - 148
e-mail	detlef.vonSeyfried@delcotex.de
date	06.07.2022

investigation report No. 22/2228

order description:	<u>Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2</u>
test samples:	"art. Halimah in different colours"
sampling:	by the client
orderer:	see address
date of order:	08.06.2022
receipt of order:	14.06.2022
date of testing:	06.07.2022

Remark: The results are valid only for the tested object. Accredited test methods are underlined. The accreditation applies for the methods listed in the annex to the certificate D-PL-17323-01-00. The valuations and Interpretations in the investigation report are not subject to accreditation. Tests conducted through co-operation partners are marked with °. All information provided by the customer, which is taken over unchecked and thus reflected in the examination report, are placed in quotation marks on the first page of the investigation report. Changes to the original investigation report are marked with a vertical line in the left margin and a revision level is added to the investigation report number. The content of this investigation report will not be passed to third persons without written approval of the orderer. The partial publication of the test report, as well as the usage for commercial process, is only allowed with a permission of the DELCOTEX Delius Techtex GmbH & Co. KG. Remnants of test material will be destroyed after 3 months. Previously stated specifications / data sheets / certificates are only characters and no warranties. Also no warranty in case of durability will be overtaken. Finally our general delivery and payment conditions are valid (please see www.textillabor.eu).

Investigation report No. 22/2228

instructions for performing

method: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

measuring conditions:

tester Atlas Xenotest alpha LM
light xenon arc beam
filtersystem type 7
sample movement interchangeable barrel
exposure time 295 h - to note 6
test equipment number: PM-Nr. 887003

test results

"art. Halimah in different colours"

article / colour	Note*
"art Halimah 101 white"	6
"art Halimah 131 grey"	5
"art Halimah 791 dark blue"	4
"art Halimah 231 sand"	5
"art Halimah 291 light brown"	5
"art Halimah 191 dark brown"	5
"art Halimah 607 lila"	4
"art Halimah 501 rosa"	4
"art Halimah 401 off white"	6
"art Halimah 121 light blue"	5-6
"art Halimah 471 yellow"	6

* The results based on using the blue scale.

Note 1 = intense colour change

Note 8 = no colour change



i.A. Detlef v. Seyfried

Laboratory/Laboratory manager

DELCOTEX Delius Techtex GmbH & Co. KG

Only the information in the signed test report is considered as binding.

Investigation report No. 22/2228

Attachment


article:

"art. Halimah in different colours"

method:

Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

art Halimah 191 dark brown
art Halimah 401 off white
art Halimah 121 light blue
art Halimah 471 yellow
art Halimah 501 rosa
art Halimah 607 lila



art Halimah 291 light brown
art Halimah 231 sand
art Halimah 791 dark blue
art Halimah 101 white
art Halimah 131 grey

