

Investigation report

SAHCO GmbH
Fr. Sarah Kemmerer

Kreuzburger Str. 17-19

DE 90471 Nürnberg

contact	Detlef von Seyfried
department	Laboratory\Laboratory
phone	+49 (0) 521/ 543 - 498
fax	+49 (0) 521/ 543 - 148
e-mail	detlef.vonsefried@delcotex.de
date	02.11.2022

investigation report No. 22/2241_1

order description:	<u>Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light:</u> <u>Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2</u>
test samples:	"art. Acca stripes in different colours"
sampling:	by the client
orderer:	see address
date of order:	08.06.2022/28.10.2022
receipt of order:	14.06.2022/28.10.2022
date of testing:	06.07.2022

Remark: The results are valid only for the tested object. Accredited test methods are underlined. The accreditation applies for the methods listed in the annex to the certificate D-PL-17323-01-00. The valuations and Interpretations in the investigation report are not subject to accreditation. Tests conducted through co-operation partners are marked with °. All information provided by the customer, which is taken over unchecked and thus reflected in the examination report, are placed in quotation marks on the first page of the investigation report. Changes to the original investigation report are marked with a vertical line in the left margin and a revision level is added to the investigation report number. The content of this investigation report will not be passed to third persons without written approval of the orderer. The partial publication of the test report, as well as the usage for commercial process, is only allowed with a permission of the DELCOTEX Delius Tectex GmbH & Co. KG. Remnants of test material will be destroyed after 3 months. Previously stated specifications / data sheets / certificates are only characters and no warranties. Also no warranty in case of durability will be overtaken. Finally our general delivery and payment conditions are valid (please see www.textillabor.eu).

Investigation report No. 22/2241_1

instructions for performing

method: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

measuring conditions:


tester Atlas Xenotest alpha LM
light xenon arc beam
filtersystem type 7
sample movement interchangeable barrel
exposure time 295 h - to note 6
test equipment number: PM-Nr. 887003

test results

“art. Acca stripes in different colours”

article / colour	Note*
"art. Acca stripe col. 101 white (weaker)"	>6
"art. Acca stripe col. 101 white (stronger)"	>6
"art. Acca stripe col. 131 light blue (weaker)"	6
"art. Acca stripe col. 131 light blue (stronger)"	6
"art. Acca stripe col. 331 sand (weaker)"	5-6
"art. Acca stripe col. 331 sand (stronger)"	5-6
"art. Acca stripe col. 551 red (weaker)"	6
"art. Acca stripe col. 551 red (stronger)"	6
"art. Acca stripe col. 731 light blue [721 light blue] (weaker)"	6
"art. Acca stripe col. 731 light blue [721 light blue] (stronger)"	6
"art. Acca stripe col. 421 light yellow (weaker)"	6
"art. Acca stripe col. 421 light yellow (stronger)"	6
"art. Acca stripe col. 771 blue [551 blue] (weaker)"	6
"art. Acca stripe col. 771 blue [551 blue] (stronger)"	6

* The results based on using the blue scale. Note 1 = intense colour change Note 8 = no colour change



i.A. Detlef von Seyfried
 Laboratory/Laboratory
 DELCOTEX Delius Techtex GmbH & Co. KG

Only the information in the signed test report is considered as binding.

Investigation report No. 22/2241

Attachment

article:
method:

"art. Acca stripes in different colours"
Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light:
Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

Art. Acca Stripe col. 331 sand

Art. Acca Stripe col. 421 light yellow

Art. Acca Stripe col. 131 light blue

Art. Acca Stripe col. 551 red

Art. Acca Stripe col. 101 white

Art. Acca Stripe col. 721 light blue

Art. Acca Stripe col. 551 blue

Art. Acca Stripe col. 331 sand

