

# Test Report

Report Number:  
123807-1-TEX



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

Gregersensvej 1  
DK-2630 Taastrup  
+45 72 20 20 00  
info@teknologisk.dk  
www.teknologisk.dk

Page 1 of 4  
Init.: CHF/LELN  
Order no.: 123807  
Encl.: 0

**Assignor:** KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

**Material:** Samples of upholstery fabric designated: Aaren. See page 2 for detailed sample description.

**Sampling:** The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 10 February 2022.

**Period:** The test took place from 11 February 2022 to 15 March 2022.

**Method:** The test methods used are referenced in connection with the results. See page 4.

**Test results:** The results are shown on page 4.

**Terms:** This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

**Place:** Danish Technological Institute, Taastrup, Environmental Technology

**Signature:** This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer  
Senior Consultant



DIGITALLY SIGNED DOCUMENT

15 March 2022

DANISH TECHNOLOGICAL INSTITUTE



**DANAK**

TEST Reg.no. 2








## Samples

Sample mark	Description	Photo
103	Sample of upholstery fabric Designated: Aaren Fibre content: 85% New wool, 10% viscose, 5% nylon	
193	Sample of upholstery fabric Designated: Aaren Fibre content: 85% New wool, 10% viscose, 5% nylon	
173	<i>Sample of upholstery fabric</i>  <i>Designated: Aaren</i>  <i>Fibre content: 85% New wool, 10% viscose, 5% nylon</i>	
133	Sample of upholstery fabric Designated: Aaren Fibre content: 85% New wool, 10% viscose, 5% nylon	
233	Sample of upholstery fabric Designated: Aaren Fibre content: 85% New wool, 10% viscose, 5% nylon	
263	Sample of upholstery fabric Designated: Aaren Fibre content: 85% New wool, 10% viscose, 5% nylon	



## Samples (*continued*)

Sample mark	Description	Photo
453	Sample of upholstery fabric Designated: Aaren Fibre content: 85% New wool, 10% viscose, 5% nylon	
683	Sample of upholstery fabric Designated: Aaren Fibre content: 85% New wool, 10% viscose, 5% nylon	
633	Sample of upholstery fabric Designated: Aaren Fibre content: 85% New wool, 10% viscose, 5% nylon	
653	Sample of upholstery fabric Designated: Aaren Fibre content: 85% New wool, 10% viscose, 5% nylon	
553	Sample of upholstery fabric Designated: Aaren Fibre content: 85% New wool, 10% viscose, 5% nylon	



## Results

### *Test of Samples of upholstery fabric designated: Aaren*

---

#### Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
103	7
193	7
173	5
133	5
233	6
263	5
453	7
683	5
633	4-5
653	7
553	7

---