



Fabrik bv
Mevr. Fatima El Madidi
Minosstraat 20
5048 CK TILBURG
Nederland

Your notice of
22-01-2019

Your reference

Date
22-05-2019

Analysis Report 19.00368.03

Modification


Required tests :
ISO 12945-2 (2000)

Determination of the resistance to pilling - Martindale

Identification number	Information given by the client	Date of receipt
T1901564	Gentle 2 Rust 0373	22-01-2019

Lies Alboort
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T1901564 - Gentle 2 Rust 0373

Determination of the resistance to pilling - Martindale

Date of ending the test 29-01-2019
 Standard used ISO 12945-2 (2000)
 Product standard EN 14465 (2003) + A1 (2006)

Deviation from the standard -
 Conditioning 20°C, relative humidity 65%
 Apparatus Martindale Wear and Abrasion Tester
 Pressure on test specimen 6,5 cN/cm²
 Abradant Crossbred worsted spun, plain woven fabric
 Number of test specimens 3
 Number of assessors 2

	Assessment at ... number of cycles			
	500	1000	2000	5000
#1	5	5	5	4-5
#2	5	5	5	4-5
#3	5	5	5	4-5

The final assessment is based on Pilling