

Test Report

Report Number:
181865-1-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 4
Init.: CHF/LELN
Order no.: 181865
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltoft

Material: Samples of upholstery fabric designated: Alle. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 21 February 2023.

Period: The test took place from 22 February 2023 to 31 March 2023.

Method: The test methods used are referenced in connection with the results. See page 4.

Test results: The results are shown from page 4 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant



DANAK

TEST Reg.no. 2








Samples

Sample mark	Description	Photo
104	Sample of upholstery fabric Designated: Alle Fibre content: 92% new wool, worsted, 8% nylon	
134	Sample of upholstery fabric Designated: Alle Fibre content: 92% new wool, worsted, 8% nylon	
164	Sample of upholstery fabric Designated: Alle Fibre content: 92% new wool, worsted, 8% nylon	
194	Sample of upholstery fabric Designated: Alle Fibre content: 92% new wool, worsted, 8% nylon	
284	Sample of upholstery fabric Designated: Alle Fibre content: 92% new wool, worsted, 8% nylon	
564	Sample of upholstery fabric Designated: Alle Fibre content: 92% new wool, worsted, 8% nylon	



Samples (continued)

Sample mark	Description	Photo
574	Sample of upholstery fabric Designated: Alle Fibre content: 92% new wool, worsted, 8% nylon	
764	Sample of upholstery fabric Designated: Alle Fibre content: 92% new wool, worsted, 8% nylon	
784	Sample of upholstery fabric Designated: Alle Fibre content: 92% new wool, worsted, 8% nylon	
884	Sample of upholstery fabric Designated: Alle Fibre content: 92% new wool, worsted, 8% nylon	
984	Sample of upholstery fabric Designated: Alle Fibre content: 92% new wool, worsted, 8% nylon	



Results

Test of Samples of upholstery fabric designated: Alle

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
104	6
134	5
164	6
194	7
284	6
564	5-6
574	5
764	6
784	6-7
884	6
984	5
