

# Test Report

Report Number:  
133937-1-TEX



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

Gregersensvej 1  
DK-2630 Taastrup  
+45 72 20 20 00  
info@teknologisk.dk  
www.teknologisk.dk

Page 1 of 5  
Init.: CHF/LELN  
Order no.: 133937  
Encl.: 0

**Assignor:** KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

**Material:** Samples of fabric designated: Sone. See page 2 for detailed sample description.

**Sampling:** The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 19 April 2022.

**Period:** The test took place from 20 April 2022 to 11 May 2022.

**Method:** The test methods used are referenced in connection with the results. See page 5.

**Test results:** The results are shown from page 5 onwards.

**Terms:** This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

**Place:** Danish Technological Institute, Taastrup, Environmental Technology

**Signature:** This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.  
  
Charlotte Fischer  
Senior Consultant








**DANAK**

TEST Reg.no. 2









## Samples

Sample mark	Description	Photo
517	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	
927	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	
117	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	
137	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	
177	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	
797	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	






## Samples (*continued*)

Sample mark	Description	Photo
397	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	
197	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	
547	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	
947	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	
957	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	
757	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	



## Samples (*continued*)

Sample mark	Description	Photo
457	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	
567	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	
767	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	
977	Sample of fabric Designated: Sone Fibre content: 100% recycled polyester	



## Results

### *Test of Samples of fabric designated: Sone*

---

#### Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
517	6
927	6-7
117	6-7
137	6
177	6
797	5-6
397	5-6
197	6
547	6-7
947	5-6
957	6-7
757	7
457	7
567	6-7
767	6
977	6

---