

Confidential Report

Our Ref: 23/60587D/01/23







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 7 February 2023

Our Ref: 23/60587D/01/23

Your Ref: ---

Page: 1 of 5

Client: Kvadrat A/S

Lundbergsvej 10 8400 Ebeltoft Denmark

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: ---

Date of Receipt: 26 January 2023

Date Test Started: 3 February 2023

Description of Sample: One sample of fabric, which was referenced by the client as;

Einar, stated to be: 70% Alpaca, 30% Mohair (backing material 100% Cotton)

Work Requested: We were asked to make the following fire test:

BS 7176: 2007 + A1:2011 (Low Hazard)

- subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited





Note: This report relates only to the items tested.



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 7 February 2023

Our Ref: 23/60587D/01/23

Your Ref:

Page: 2 of 5

Client: Kvadrat A/S

Specification BS 7176: 2007 + A1:2011 Resistance to Ignition of Upholstered Furniture for nondomestic seating by testing composites using BS EN 1021:2006 Furniture - Assessment of the ignitability of upholstered furniture Parts 1 and 2 (Low Hazard).

Pre-Treatment

The material received no pre-treatment as the fabric is stated not to be FR treated.

Conditioning

The materials for testing to Source 0 and 1 were conditioned for a minimum of 24 hours and tested in the environments specified in Clause 7 of BS EN 1021-1 & 2:2006.

Foam Used

The sample was tested over Non FR polyurethane foam with a density of approximately 20-22kg/m³.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

7 February 2023 Date:

Our Ref: 23/60587D/01/23 Your Ref:

> Page: 3 of 5

Client: Kvadrat A/S

Testing to BS EN 1021-1:2006 – Source 0 – Cigarette

The sample was tested in accordance with BS EN 1021-1:2006.

The test results relate only to the ignitability of the combustion of upholstery composites under the particular conditions of test stated, they are not intended as a means of assessing he full potential fire hazard of the materials of products in use.

Results

Smouldering criteria	Specimen No.	
	1	2
Unsafe escalating combustion	No	No
Testing assembly consumed	No	No
Smoulders to extremities/full thickness	No	No
Smoulders more than 1 hour	No	No
In final examination, presence of progressive smouldering	No	No

Flaming criteria	1	2
Occurrence of flames	No	No
Specimen Result	Non-Ignition (NI)	Non-Ignition (NI)
(Ignition or Non-ignition)	. ,	, ,

Any "Yes" in smouldering or flaming criteria means Ignition

Cigarette Test Result PASS







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

7 February 2023 Date:

Our Ref: 23/60587D/01/23 Your Ref:

> Page: 4 of 5

Client: **Kvadrat A/S**

BS EN 1021-2: 2006 – Source 1 – Butane Flame (Match)

The sample was tested in accordance with BS EN 1021-2:2006.

The test results relate only to the ignitability of the combustion of upholstery composites under the particular conditions of test stated, they are not intended as a means of assessing he full potential fire hazard of the materials of products in use.

Results

	Specimen No.	
Smouldering criteria	1	2
Unsafe escalating combustion	No	No
Testing assembly consumed	No	No
Smoulders to extremities/full thickness	No	No
Smoulders more than 1 hour	No	No
In final examination, presence of	No	No
progressive smouldering		

Flaming criteria	1	2
Unsafe escalating combustion	No	No
Testing assembly consumed	No	No
Flames to extremities/full thickness	No	No
Flames longer than 120 seconds	No	No
Specimen Result	NI	NI
Ignition (I) / Non Ignition (NI)		

Any "Yes" in smouldering or flaming criteria means Ignition

Match Test Result PASS







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 7 February 2023

Our Ref: 23/60587D/01/23

Your Ref:

Page: 5 of 5

Client: Kvadrat A/S

Conclusion

The combination of materials meets BS 7176:2007+A1:2011 for Low Hazard.

See BS 7176: 2007 + A1: 2011 Clause 6 for labelling and identification requirements. The test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test stated (BS EN 1021-1: 2006, BS EN 1021-2: 2006 and BS 5852: 2006 respectively); they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (https://www.bttg.co.uk/about-us/decision-rules-policy/) for further information.

Uncertainty Budget

Measurements: ±2mm Timings: ±2 seconds.

Reported by:..... B Bland, Technical Customer Services Officer

Countersigned by:... P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.



