

Test Report

Report Number:
156784-2-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 5
Init.: CHF/LELN
Order no.: 156784
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

Material: Samples of upholstery fabric designated: Einar. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 23 September 2022.

Period: The test took place from 27 September 2022 to 24 October 2022.

Method: The test methods used are referenced in connection with the results. See page 5.

Test results: The results are shown from page 5 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant








DANAK

TEST Reg.no. 2








Samples

Sample mark	Description	Photo
127	Sample of upholstery fabric Designated: Einar Fibre content: 70% Alpaca, 30% Mohair, backing 100% cotton	
137	Sample of upholstery fabric Designated: Einar Fibre content: 70% Alpaca, 30% Mohair, backing 100% cotton	
197	Sample of upholstery fabric Designated: Einar Fibre content: 70% Alpaca, 30% Mohair, backing 100% cotton	
187	Sample of upholstery fabric Designated: Einar Fibre content: 70% Alpaca, 30% Mohair, backing 100% cotton	
427	Sample of upholstery fabric Designated: Einar Fibre content: 70% Alpaca, 30% Mohair, backing 100% cotton	






Samples (*continued*)

Sample mark	Description	Photo
527	Sample of upholstery fabric Designated: Einar Fibre content: 70% Alpaca, 30% Mohair, backing 100% cotton	
557	Sample of upholstery fabric Designated: Einar Fibre content: 70% Alpaca, 30% Mohair, backing 100% cotton	
577	Sample of upholstery fabric Designated: Einar Fibre content: 70% Alpaca, 30% Mohair, backing 100% cotton	
587	Sample of upholstery fabric Designated: Einar Fibre content: 70% Alpaca, 30% Mohair, backing 100% cotton	
687	Sample of upholstery fabric Designated: Einar Fibre content: 70% Alpaca, 30% Mohair, backing 100% cotton	



Samples (*continued*)

Sample mark	Description	Photo
937	Sample of upholstery fabric Designated: Einar Fibre content: 70% Alpaca, 30% Mohair, backing 100% cotton	
987	Sample of upholstery fabric Designated: Einar Fibre content: 70% Alpaca, 30% Mohair, backing 100% cotton	
677	Sample of upholstery fabric Designated: Einar Fibre content: 70% Alpaca, 30% Mohair, backing 100% cotton	



Results

Test of Samples of upholstery fabric designated: Einar

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
127	5
137	6
197	7
187	4-5
427	7
527	5
557	7
577	6-7
587	6
687	7
937	4
987	7
677	6
