



TEST REPORT

Client: SAHCO UK
 G24 Design Centre Chelsea Harbour
 London
 SW10 0XE

Entry No: 78444

Date received: 26/08/2016

Client's Description: Sample of fabric: Mountain C037-01

Test Required: Flammability in accordance with BS 5852 ignition source 5

Pre-treatment: None

Conditioning: A minimum of 96 hours at 50+/-5% Relative Humidity, 23+/-2°C

Date Tests Completed: 06/09/2016

Method of Test: BS 5852: 2006 Clause 11 (composites)

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source	Observations	Result
5 (Wood Crib)	Flaming ceased within the specified ten minute period after ignition of the crib and no progressive smouldering occurred.	PASS

Note: A 35 kg/m³ CMHR foam (Carpenters RX36-125) was used as the filling

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein



Dale Brockbank
 Materials Testing Manager
 06 September 2016

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
 - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104