

Investigation report

SAHCO GmbH
Fr. Sarah Kemmerer
Kreuzburger Str. 17-19

DE 90471 Nürnberg

contact Alicja Rösler
department Laboratory\Lab-manager
phone +49 (0) 5206/9107 -57
fax +49 (0) 5206/9107 -34
e-mail alicja.roesler@delcotex.de
date 16.12.2020

investigation report No. 20/3968

order description: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2
test samples: "Art. 600725 Elle, in 14 colours"
sampling: by the client
orderer: see address
date of order: 12.11.2020
receipt of order: 17.11.2020
date of testing: 16.12.2020

Remark: The results are valid only for the tested object. The accreditation applies for the methods listed in the annex to the certificate D-PL-17323-01-00. Accredited test methods are underlined. The valuations and Interpretations in the investigation report are not subject to accreditation. Tests conducted through co-operation partners are marked with °. All information provided by the customer, which is taken over unchecked and thus reflected in the examination report, are placed in quotation marks on the first page of the investigation report. The content of this investigation report will not be passed to third persons without written approval of the orderer. The partial publication of the test report, as well as the usage for commercial process, is only allowed with a permission of the DELCOTEX Delius Techtex GmbH & Co. KG. Remnants of test material will be destroyed after 3 months. Previously stated specifications / data sheets / certificates are only characters and no warranties. Also no warranty in case of durability will be overtaken. Finally our general delivery and payment conditions are valid (please see www.textillabor.eu).

Investigation report No. 20/3968

instructions for performing

method: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

measuring conditions:

tester Atlas Xenotest alpha LM

light xenon arc beam

filtersystem type 7

sample movement interchangeable barrel

exposure time 240 h - to note 6


test equipment number: PM-Nr. 887003

test results

"Art. 600725 Elle"

article / colour	Note*
"art. 600725 Elle, col. 0230"	>6
"art. 600725 Elle, col. 0200"	>6
"art. 600725 Elle, col. 0220"	>6
"art. 600725 Elle, col. 0280"	6
"art. 600725 Elle, col. 0290"	6
"art. 600725 Elle, col. 0390"	>6
"art. 600725 Elle, col. 0530"	>6
"art. 600725 Elle, col. 0480"	>6
"art. 600725 Elle, col. 0350"	>6
"art. 600725 Elle, col. 0680"	>6
"art. 600725 Elle, col. 0150"	6
"art. 600725 Elle, col. 0750"	>6
"art. 600725 Elle, col. 0180"	6
"art. 600725 Elle, col. 0950"	>6

* The results based on using the blue scale. Note 1 = intense colour change, Note 8 = no colour change



i.A. Alicia Rösler

Laboratory/Lab-manager

DELCOTEX Delius Techtex GmbH & Co. KG

Only the information in the signed test report is considered as binding.

Investigation report No. 20/3968

Attachment

article: "Art. 600725 Elle "

method: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

col.: 0680

col.: 0390

col.: 0350

col.: 0180

col.: 0750



col.: 0530

col.: 0230

col.: 0150

col.: 0220

col.: 0280



Investigation report No. 20/3968

Attachment

article: "Art. 600725 Elle "

method: Textiles - Tests for colour fastness - Part B02: Colour fastness to artificial light: Xenon arc fading lamp test DIN EN ISO 105-B02 (2014-11) method 2

col.: 0950

col.: 0480

col.: 0290

col.: 0200

