Test Report

Report Number: 157659-1-TEX



DANISH TECHNOLOGICAL INSTITUTE

Gregersensvej 1 DK-2630 Taastrup +45 72 20 20 00 info@teknologisk.dk www.teknologisk.dk

Page 1 of 4 Init.: CHF/LELN Order no.: 157659 Encl.: 0

| Assignor: | KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltoft |
|---------------|--|
| Material: | Samples of curtain fabric designated: Broken Twill Sheer. See page 2 for detailed sample description. |
| Sampling: | The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 29 September 2022. |
| Period: | The test took place from 3 October 2022 to 31 October 2022. |
| Method: | The test methods used are referenced in connection with the results. See page 4. |
| Test results: | The results are shown from page 4 onwards. |
| Terms: | This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent. |
| Place: | Danish Technological Institute, Taastrup, Environmental Technology |
| Signature: | This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature. |
| | Charlotte Fischer Senior Consultant |





Samples

| Sample mark | Description | Photo |
|-------------|---|-------|
| 950 | Samples of curtain fabric Designated: Broken Twill Sheer Fibre content: 75% Trevira CS, 25% recycled Trevira CS | |
| 100 | Samples of curtain fabric Designated: Broken Twill Sheer Fibre content: 75% Trevira CS, 25% recycled Trevira CS | |
| 110 | Samples of curtain fabric Designated: Broken Twill Sheer Fibre content: 75% Trevira CS, 25% recycled Trevira CS | |
| 130 | Samples of curtain fabric Designated: Broken Twill Sheer Fibre content: 75% Trevira CS, 25% recycled Trevira CS | |
| 230 | Samples of curtain fabric Designated: Broken Twill Sheer Fibre content: 75% Trevira CS, 25% recycled Trevira CS | |



Samples (continued)

| Sample mark | Description | Photo |
|-------------|---|-------|
| 650 | Samples of curtain fabric Designated: Broken Twill Sheer Fibre content: 75% Trevira CS, 25% recycled Trevira CS | |
| 740 | Samples of curtain fabric Designated: Broken Twill Sheer Fibre content: 75% Trevira CS, 25% recycled Trevira CS | |
| 760 | Samples of curtain fabric Designated: Broken Twill Sheer Fibre content: 75% Trevira CS, 25% recycled Trevira CS | |
| 450 | Samples of curtain fabric Designated: Broken Twill Sheer Fibre content: 75% Trevira CS, 25% recycled Trevira CS | |
| 680 | Samples of curtain fabric Designated: Broken Twill Sheer Fibre content: 75% Trevira CS, 25% recycled Trevira CS | |
| 980 | Samples of curtain fabric Designated: Broken Twill Sheer Fibre content: 75% Trevira CS, 25% recycled Trevira CS | |



Results

Test of Samples of curtain fabric designated: Broken Twill Sheer

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2 1-8 scale, 8 best rating Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

| Sample mark | Colour fastness |
|-------------|-----------------|
| 950 | 5-6 |
| 100 | 7 |
| 110 | 7 |
| 130 | 6 |
| 230 | 6 |
| 650 | 6 |
| 740 | 6 |
| 760 | 6 |
| 450 | 6 |
| 680 | 5-6 |
| 980 | 5-6 |