

# Test Report

Report Number:  
190729-12-TEX



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

Gregersensvej 1  
DK-2630 Taastrup  
+45 72 20 20 00  
info@teknologisk.dk  
www.teknologisk.dk

Page 1 of 4  
Init.: CHF/LELN  
Order no.: 190729  
Encl.: 0

**Assignor:** KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltoft

**Material:** Samples of curtain fabric designated: Fil-a-Fil, item 5511. See page 2 for detailed sample description.

**Sampling:** The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 20 April 2023.

**Period:** The test took place from 21 April 2023 to 17 May 2023.

**Method:** The test methods used are referenced in connection with the results. See page 4.

**Test results:** The results are shown from page 4 onwards.

**Terms:** This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

**Place:** Danish Technological Institute, Taastrup, Environmental Technology

**Signature:** This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.  
  
Charlotte Fischer  
Senior Consultant









**DANAK**

TEST Reg.no. 2



## Samples

Sample mark	Description	Photo
0149 White	Sample of curtain fabric Designated: Fil-a-Fil Composition: 65% LI, 28% CLY, 7% SE	
0149 Dark Grey	Sample of curtain fabric Designated: Fil-a-Fil Composition: 65% LI, 28% CLY, 7% SE	
0149 Light Grey	Sample of curtain fabric Designated: Fil-a-Fil Composition: 65% LI, 28% CLY, 7% SE	
0249 Light Beige	Sample of curtain fabric Designated: Fil-a-Fil Composition: 65% LI, 28% CLY, 7% SE	
0249 Brown	Sample of curtain fabric Designated: Fil-a-Fil Composition: 65% LI, 28% CLY, 7% SE	
0249 Dark Grey	Sample of curtain fabric Designated: Fil-a-Fil Composition: 65% LI, 28% CLY, 7% SE	



## Samples (*continued*)

Sample mark	Description	Photo
0669 Purple	Sample of curtain fabric Designated: Fil-a-Fil Composition: 65% LI, 28% CLY, 7% SE	
0669 Brown	Sample of curtain fabric Designated: Fil-a-Fil Composition: 65% LI, 28% CLY, 7% SE	
0669 Black	Sample of curtain fabric Designated: Fil-a-Fil Composition: 65% LI, 28% CLY, 7% SE	
0969 Black	Sample of curtain fabric Designated: Fil-a-Fil Composition: 65% LI, 28% CLY, 7% SE	
0969 Green	Sample of curtain fabric Designated: Fil-a-Fil Composition: 65% LI, 28% CLY, 7% SE	
0969 Brown	Sample of curtain fabric Designated: Fil-a-Fil Composition: 65% LI, 28% CLY, 7% SE	



## Results

### *Test of Samples of curtain fabric designated: Fil-a-Fil, item 5511*

---

#### Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
0149 White	6
0149 Dark Grey	7
0149 Light Grey	6
0249 Light Beige	7
0249 Brown	6
0249 Dark Grey	6
0669 Purple	6
0669 Brown	6
0669 Black	7
0969 Black	7
0969 Green	6
0969 Brown	5

---