

Kvadrat A/S Lundbergsvej 10 8400 Ebeltoft Denmark Your Reference Customer Number 50136 Contact Person Novotná Martina E-Mail mano@kvadrat.org

Vienna / 22.05.2023 / guse

# Test Report VN736 220835.4

### Application

Testing and classification of the burning behaviour according EN 13773.

### **Test Material**

Inch

The test material used for testing was made anonymous for laboratory purposes. A detailed sample list is included in the document.

**Issuing** Original Issuing, 22.05.2023

Number Of Included Pages: 7

OETI - Institut fuer Oekologie, Technik und Innovation GmbH

Junth Sens

Günther Sereinig Customer Service Officer





OETI - Institut fuer Oekologie, Technik und Innovation GmbH | Siebenhirtenstrasse 12A, Objekt 8, 1230 Vienna, Austria tel +43 1 5442543-0 | e-mail office@oeti.biz | www.oeti.biz | FN 326826 b | VAT No. ATU65149029 | EORI ATEOS1000015903 Member of TESTEX Group



### 1 Application

Date of Order	Scope of Order			
20.04.2023	Description Of Specimen - Textile Fabrics - DIN 60000			
	Ignitability Vertical Orientated Specimen - EN 1101 (1995-11)			
	Flame Spread of Vertical Oriented Specimen - supplied cond EN 13772 (2011-0			
	Dropping Behaviour - supplied condition - EN 13772 (2011-01)			
	Classification Of Burning Behaviour Of Curtains And Drapes - EN 13773			

# 2 Samples

No.	Receipt	Sample Identification
1	25.04.2023	Inch

(Unless otherwise stated samples are provided by the customer.)

### 3 Tests Performed / Results

### \*Description Of Specimen - Textile Fabrics DIN 60000

Tested sample:

#1 Inch

Type of fibre:	100% Trevira CS		
	(declaration by the applicant)		
Technological description:	gauze fabric		

According to the current version of the relevant European Directives, fibre materials with a mass percentage of

< 2 % are not specified.



# Ignitability Vertical Orientated Specimen EN 1101 (1995-11)

Tested sample:	#1 Inch
Test climate:	
- Temperature [°C]:	25
- rel. Humidity: [%]:	33
Specimen size [mm]:	200x80
Test gas:	Propane
Mode of ignition:	edge flame treatment
Pretreatment:	None
Deviation from	None
standard:	

Longitudinal direction			Cross	direction	
I avaitie a time e	Number of			Number of	
Ignition time	Ignitions	No ignitions	Ignition time	Ignitions	No ignitions
1 s	0	1	1 s	0	1
2 s	0	1	2 s	0	1
3 s	0	1	3 s	0	1
4 s	0	1	4 s	0	1
5 s	0	1	5 s	0	1
10 s	0	1	10 s	0	1
15 s	0	1	15 s	0	1
20 s	0	5	20 s	0	5

Middle ignition time [s]	> 20	Middle ignition time [s]	> 20

# Minimum ignition time [s]

> 20

Measurement uncertainty [%]: 13.76



### Flame Spread of Vertical Oriented Specimen - supplied cond. EN 13772 (2011-01)

Tested sample:	#1 Inch
Conditioning climate:	20±2 °C/ 65± 5 % relative humidity
Test gas:	Propan
Pretreatment:	None, test was carried out in supplied condition
Deviation from	none
standard:	none

Note: According to the specification of the applicant the tested sample can not be washed, therefore it was tested in supplied condition

Sample	exposed surface	1st marker thread severed	3rd marker thread severed	inflammatio	n start of n to burning n of the 3rd marker thread	destroyed length	flaming debris
				[s]	[s]	[cm]	
Longitudina	Longitudinal direction						
1	right	No	No	0	0	14.0	No
2	left	No	No	0	0	15.0	No
3	right	No	No	0	0	13.0	No
4	right	No	No	0	0	16.0	No
Cross direc	Cross direction						
1	right	No	No	0	0	15.0	No
2	left	No	No	0	0	12.0	No
3	right	No	No	0	0	14.0	No
4	right	No	No	0	0	14.0	No

Measurement uncertainty [%]:

17

Precision: With an interlaboratory test with 16 textile samples in 11 European laboratories it showed up that the determined results are reproducible and repeatable. Between all laboratories agreeing results showed up. The uncertainty of the measurement [u] corresponds therefore to the dispersion of the individual values of the respective examination.



# Dropping Behaviour - supplied condition EN 13772 (2011-01)

Tested sample: #1 Inch

none

Pretreatment: none

Deviation from

standard:

Comment: The determination of dropping behaviour for curtains classified as Class 1 or 2 is done according to EN 13772.

Loi	ngitudinal direct	ion		Cross direction	
Sample	Number of drops	Igniting dropping	Sample	Number of drops	Igniting dropping
1	0	No	1	0	No
2	0	No	2	0	No
3	0	No	3	0	No
4	0	No	4	0	No



### \*Classification Of Burning Behaviour Of Curtains And Drapes EN 13773

Tested sample: #1 Inch

Determination of the ignitability according to EN	no ignition	
Determination of the flame spread of vertical	1st Markerthread	not broken
orientated specimen according to EN 13772 -	3rd Markerthread	not broken
supplied condition	Flaming debris	none
Determination of the flame spread of vertical	1st Markerthread	-
orientated specimen according to EN 13772 -	3rd Markerthread	-
after cleaning	Flaming debris	-
max. number of drops fall down during EN 13772	none	
Drops caused ignition of filter paper	none	

#### Classification of burning behaviour

According to the classification criteria of EN 13773 the tested specimen can be classified as:

Class 1

#### Classification of dropping behaviour

The tested specimen can be classified as

### Not dropping

Not dropping behaviour corresponds in accordance with the former standard ÖNORM B 3800 part 1 point 6.1 to the drop class "Tr1- nicht tropfend"



#### 4 Remarks

#### Period of Validity

There are no regulations concerning duration of validity in the individual test standards. As the results of the examinations refer only to the submitted and examined samples, the report is valid for these for an unlimited period. A period of validity specified as part of an expert evaluation is in the discretion of the consultant or OETI. The applicability of results and expert evaluations for materials not tested is in the responsibility of the applicant. Whereby an apportionment of results as well as any specified period of validity can only be done for identically constructed products and only as long as the product is produced unchanged. Possible national or international restrictions concerning the terms of usability of test and classification reports have to be considered; this is not the responsibility of the test laboratory.

#### Sample Material

Results of performed tests only refer to the sample material provided. The testing period is defined as timeframe between receipt of samples and issue date of test report. Without explicit written other agreement testing is destructive and the sample material is transferred to the property of OETI, which is entitled to freely decide on storage and disposal.

#### Issuing

This test report is only issued as a PDF. Translations will be marked accordingly on the cover sheet.

#### **Quality Management, Accreditation And Notification**

All tests and services are performed under a quality management system according to EN ISO/IEC 17025. OETI is accredited as Testing Laboratory and Certification Body for products. It also is a Notified Body (NB0534). (see http://ec.europa.eu/enterprise/newapproach/nando/). Accreditation was provided by Akkreditierung Austria. The scope of accreditation is listed on www.oeti.biz. Due to the system for the mutual recognition of national accreditations (ILAC/IAF), this accreditation is valid worldwide.

Statements of conformity are based on the specifications of the specified standard. The "simple acceptance rule" applies, that means the measurement uncertainty is stated for the statement of conformity, but not taken into account.

In this report individual non-accredited test procedures are marked with \*. Nevertheless, the analysis was also carried out for these parameters at the same level of quality as for the accredited parameters.

According to the decree on the use of the accreditation mark ("AkkZV") the accredited Conformity Assessment Body is the only one to use the accreditation mark. Application of the registration number of the Notified Body: As to personal protective equipment (PPE) the requirements of Regulation (EU) 2016/425 have to be kept. With construction products the application is only permitted within the declaration of performance for CE-marking.

#### **Copyright And Usage Notes**

It is pointed out, that any alterations, amendments or falsifications of reports not authorized by the issuer of the report will be prosecuted as civil and criminal offences; this especially to the appropriate requirements of ABGB, UrhG, UWG and criminal law and their respective international equivalents. Reports are protected under international copyright laws. Written consent of the OETI GmbH is required for publications (also in excerpt) and reference to tests for public relation purposes. Reports may only be reproduced in full length.

End of Report