Test Report

Report Number: 190729-4-TFX



INSTITUTE

Gregersensvej 1 DK-2630 Taastrup +45 72 20 20 00 info@teknologisk.dk www.teknologisk.dk

Page 1 of 3 Init.: CHF/LELN Order no.: 190729

Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltoft

Material: Samples of curtain fabric designated: Rhythm, item 5517. See page 2 for detailed sample

description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the

assignor and received at Danish Technological Institute on 20 April 2023.

Period: The test took place from 21 April 2023 to 17 May 2023.

Method: The test methods used are referenced in connection with the results. See page 3.

Test results: The results are shown from page 3 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC

17025:2017) and in accordance with the General Terms and Conditions of Danish

Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The

date of issue appears from the digital signature.

Charlotte Fischer Senior Consultant





Samples

Sample mark	Description	Photo
105	Sample of curtain fabric Designated: Rhythm Composition: 50% TCS rec, 50% TCS	
155	Sample of curtain fabric Designated: Rhythm Composition: 50% TCS rec, 50% TCS	
355	Sample of curtain fabric Designated: Rhythm Composition: 50% TCS rec, 50% TCS	
295	Sample of curtain fabric Designated: Rhythm Composition: 50% TCS rec, 50% TCS	
605	Sample of curtain fabric Designated: Rhythm Composition: 50% TCS rec, 50% TCS	
965	Sample of curtain fabric Designated: Rhythm Composition: 50% TCS rec, 50% TCS	

190729-4-TEX Page 2 of 3



Results

Test of Samples of curtain fabric designated: Rhythm, item 5517

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
105	7
155	7
355	7
295	7
605	7
965	6

190729-4-TEX Page 3 of 3