

**Fabrik bv**  
**Mevr. Renee Merckx**  
**Minosstraat 20**  
**5048 CK TILBURG**  
**Nederland**

**Your notice of**  
07-01-2014

**Your reference**

**Date**  
11-07-2019

## Analysis Report 14.00065.03


Required tests :

**ISO 12947-2 (1998)/cor.1 (2002)      Determination of the abrasion resistance - Martindale**

Identification number	Information given by the client	Date of receipt
T1319013	Triangle Chalk	09-12-2013

Joceleyne Coreelman  
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



**Reference: T1319013r - Triangle Chalk**

**Determination of the abrasion resistance - Martindale**

Date of ending the test 13-01-2014  
Standard used ISO 12947-2 (1998)/cor.1 (2002)

Deviation from the standard -  
Conditioning 20°C, relative humidity 65%  
Apparatus Martindale Wear and Abrasion Tester  
Pressure on test specimen 12 kPa  
Abradant Crossbred worsted spun, plain woven fabric  
Type of the felt Woven felt  
Number of test specimens 4

Test end point Knitted - 1 loop completely damaged

Specimen	Number of cycles	Final result
#1	80 000	70 000
#2	80 000	70 000
#3	90 000	80 000
#4	90 000	80 000
Average	85 000	75 000

Annex 1 Tested specimens enclosed



## Sample history

**T1319013r**                      **Triangle Chalk**  
Sample reused from order A1305784