

# Test Report

Report No.: A880006-4



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

**Assignor:** Kvadrat A/S  
Lundbergsvej 10  
8400 Ebeltøft  
Attn.: Lone Henriksen

Page 1 of 1  
LeIn/Chf  
Order no.:880006  
No. of appendices: 1

**Subject:** Upholstery fabric Parkland 151, Fibre content: 100 % Trevira CS (as per info from the assigner).



**Sampling:** The test material was sampled by the client and received at the Danish Technological Institute 02.07.2019

**Method:** See Appendix 1.

**Period:** The testing was completed 22.07.2019

**Result:** Individual results appear from Appendix 1.

**Storage:** The test material will be destroyed after 6 months, unless otherwise agreed.

**Terms:** The accredited test was carried out according to DANAK's general conditions see [www.danak.dk](http://www.danak.dk) and according to the General Terms and Conditions regarding Commissioned Work Accepted by the Danish Technological Institute, which apply at the time of signing the agreement. The test is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

**Date/place:** 02.09.2019, Danish Technological Institute, Wood and Biomaterials, Textile, Taastrup

**Signature:** Test responsible

Co-signatory



Report no.: A880006-4  
 Appendix: 1  
 Page: 1 of 1  
 Initials: LelN/Chf

Test Methods	Results
<p><b>Abrasion resistance - Martindale Part 2: Determination of specimen breakdown</b>            DS/EN ISO 12947-2:2016            Mass: 795 g            Nominal pressure: 12 kPa            End-point: Two broken threads            Colour change (1-5 scale, 5 best rating)            ISO 105-A02:1993            Test conditions: 21°C, 65%RH</p>	<p>Individual re- &gt;100 000 - &gt;100 000 - &gt;100 000 rubs            sults:            Colour change: 3-4 after 6000 rubs</p>