

Test Report

Revision 1

Report Number:
190729-14-TEX rev. 1



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 3
Init.: CHF/LELN
Order no.: 190729
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

Material: Samples of curtain fabric designated: Paper, item 5527. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 20 April 2023.

Period: The test took place from 21 April 2023 to 17 May 2023.

Method: The test methods used are referenced in connection with the results. See page 3.

Test results: The results are shown from page 3 onwards.

Remarks: This report replaces Report no. 190729-14, 204763-1 and 205948-2 of 17.05.2023/ 27.07.2023/07.08.2023. The results for sample no. 140 and 700 has been changed due to new samples tested the 27.07.2023 and 07.08.2023. Customer has made changes and would like the results in 1 report.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant








DANAK

TEST Reg.no. 2



Samples

Sample mark	Description	Photo
110	Sample of curtain fabric Designated: Paper Composition: 100% PI	
140	Sample of curtain fabric Designated: Paper Composition: 100% PI	
200	Sample of curtain fabric Designated: Paper Composition: 100% PI	
700	Sample of curtain fabric Designated: Paper Composition: 100% PI	
800	Sample of curtain fabric Designated: Paper Composition: 100% PI	



Results

Test of Samples of curtain fabric designated: Paper, item 5527

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
110	5
140	3-4
200	6
700	3
800	3-4
