



Feabrik bv
Minosstraat 20
5048 CK TILBURG
Netherlands

Your notice of
30-09-2021

Your reference

Date
18-10-2021

Analysis Report 21.06101.01


Required tests :

IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8 **Fire tests - Test for upholstered furniture - smouldering cigarette test**
IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8 **Fire tests - Test for upholstered furniture - Match flame equivalent**

| Sample id | Information given by the client | Date of receipt |
|-----------|---------------------------------|-----------------|
| T2120943 | MIZMAZE | 30-09-2021 |

Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2120943 - MIZMAZE

IMO upholstered furniture

Information given by the client

Type of furniture

Seat / sofa / office chair

Fabric

Composition

30% new wool / 10% nylon // 60% polyester filling

Structure

Knitted

Number of threads - warp

NA

Number of threads - weft

NA

Yarn count - warp

Front: nm 28/1

Yarn count - weft

Back: pes 167 dtex

Thickness in mm

4

Weight g/m²

570

Colour

Light grey

Not FR treated

yes



Reference: T2120943 - MIZMAZE

Fire tests - Test for upholstered furniture - smouldering cigarette test

| | |
|-----------------------------|--|
| Date of ending the test | 18-10-2021 |
| Standard used | IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8 |
| Deviation from the standard | - |
| Conditioning | 23°C, relative humidity 50% |
| Filling | T 23140 (Recticel) * - non-fire retardant foam - $\pm 22 \text{ kg/m}^3$ * standard non-FR PU-foam (as indicated in Appendix 2 and 3 of Part 8) |
| Dimension of the specimens | 800 mm x 650 mm x 3 mm |
| Weight (g/m ²) | 595 |


Ignition source: smouldering cigarette with the following specifications

Length: $(70 \pm 4) \text{ mm}$

Diameter: $(8.0 \pm 0.5) \text{ mm}$

Mass: $(0.95 \pm 0.15) \text{ g}$

Smouldering rate: $(11.0 \pm 4.0) \text{ min} / 50 \text{ mm}$



| | 1 | 2 |
|--|--------------|--------------|
| Smouldering criteria | | |
| Unsafe escalating combustion | no | no |
| Test assembly consumed | no | no |
| Smoulders to extremities | no | no |
| Smoulders through thickness | no | no |
| Smoulders more than 1 hour | no | no |
| Final examination / active smouldering | no | no |
| Flaming criteria | | |
| Occurrence of flames | no | no |
| Additional observations | | |
| Maximum extent of damage from the ignition source (mm) | 0 | 0 |
| | | |
| | non-ignition | non-ignition |

Conclusion Pass


The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.



Reference: T2120943 - MIZMAZE

Fire tests - Test for upholstered furniture - Match flame equivalent

| | |
|-----------------------------|--|
| Date of ending the test | 18-10-2021 |
| Standard used | IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 8 |
| Deviation from the standard | - |
| Conditioning | 23°C, relative humidity 50% |
| Filling | T 23140 (Recticel) * - non-fire retardant foam - $\pm 22 \text{ kg/m}^3$ * standard non-FR PU-foam (as indicated in Appendix 2 and 3 of Part 8) |
| Dimension of the specimens | 800 mm x 650 mm x 3 mm |
| Weight (g/m^2) | 595 |
| Flame application time (s) | 20 |



| | 1 | 2 |
|--|--------------|--------------|
| Smouldering criteria | | |
| Unsafe escalating combustion | no | no |
| Test assembly consumed | no | no |
| Smoke/heat/glowing more than 120 s | no | no |
| Final examination / active smouldering | no | no |
| Flaming criteria | | |
| Unsafe escalating combustion | no | no |
| Test assembly consumed | no | no |
| Flaming > 120 s | no | no |
| Afterflame time (s) | 0 | 0 |
| Additional observations | | |
| Afterglow time (s) | 0 | 0 |
| Maximum extent of damage from the ignition source (mm) | 35 | 45 |
| | | |
| | non-ignition | non-ignition |

Conclusion Pass

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.