

Test Report

Revision 1

Report Number:
128057-1-TEX rev. 1



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 5
Init.: CHF/LELN
Order no.: 128057
Encl.: 0

Assignor:	KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltoft
Material:	Samples of upholstery fabric designated: Sport 100% Ocean Bound Polyester. See page 2 for detailed sample description.
Sampling:	The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 9 March 2022.
Period:	The test took place from 9 March 2022 to 1 April 2022.
Method:	The test methods used are referenced in connection with the results. See page 5.
Test results:	The results are shown from page 5 onwards.
Remarks:	This report replaces Report no. 128057-1 of 01.04.2022. Change of name on the fabrics requested by the customer.
Terms:	This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.
Place:	Danish Technological Institute, Taastrup, Environmental Technology
Signature:	This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature. Charlotte Fischer Senior Consultant



DANAK

TEST Reg.no. 2



Samples

Sample mark	Description	Photo
823	Sample of upholstery fabric Designated: Sport Fibre content: 100% Ocean Bound Polyester	
553	Sample of upholstery fabric Designated: Sport Fibre content: 100% Ocean Bound Polyester	
543	Sample of upholstery fabric Designated: Sport Fibre content: 100% Ocean Bound Polyester	
243	Sample of upholstery fabric Designated: Sport Fibre content: 100% Ocean Bound Polyester	
443	Sample of upholstery fabric Designated: Sport Fibre content: 100% Ocean Bound Polyester	
153	Sample of upholstery fabric Designated: Sport Fibre content: 100% Ocean Bound Polyester	




Samples (*continued*)

Sample mark	Description	Photo
213	Sample of upholstery fabric Designated: Sport Fibre content: 100% Ocean Bound Polyester	
613	Sample of upholstery fabric Designated: Sport Fibre content: 100% Ocean Bound Polyester	
783	Sample of upholstery fabric Designated: Sport Fibre content: 100% Ocean Bound Polyester	
113	Sample of upholstery fabric Designated: Sport Fibre content: 100% Ocean Bound Polyester	
173	Sample of upholstery fabric Designated: Sport Fibre content: 100% Ocean Bound Polyester	
253	Sample of upholstery fabric Designated: Sport Fibre content: 100% Ocean Bound Polyester	
643	Sample of upholstery fabric Designated: Sport Fibre content: 100% Ocean Bound Polyester	



Samples (*continued*)

Sample mark	Description	Photo
183	Sample of upholstery fabric Designated: Sport Fibre content: 100% Ocean Bound Polyester	



Results

Test of Samples of upholstery fabric designated: Sport 100% Ocean Bound Polyester

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
823	6-7
553	6-7
543	7
243	6-7
443	7
153	7
213	7
613	7
783	7
113	6
173	7
253	6-7
643	6-7
183	7

Test Report

Report Number:
138474-1-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 3
Init.: CHF/LELN
Order no.: 138474
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

Material: Sample of fabric designated: Sport. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 11 May 2022.

Period: The test took place from 12 May 2022 to 10 June 2022.

Method: The test methods used are referenced in connection with the results. See page 3.

Test results: The results are shown from page 3 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant



DIGITALLY SIGNED DOCUMENT

10 June 2022

DANISH TECHNOLOGICAL INSTITUTE









DANAK

TEST Reg.no. 2



Samples

Sample mark	Description	Photo
123 M/2	Sample of fabric Designated: Sport Fibre content: 100% Ocean bound polyester	
133 C/5	Sample of fabric Designated: Sport Fibre content: 100% Ocean bound polyester	
713 N/9	Sample of fabric Designated: Sport Fibre content: 100% Ocean bound polyester	
743	Sample of fabric Designated: Sport Fibre content: 100% Ocean bound polyester	
923 A/14	Sample of fabric Designated: Sport Fibre content: 100% Ocean bound polyester	
943 M/13	Sample of fabric Designated: Sport Fibre content: 100% Ocean bound polyester	



Results

Test of Sample of fabric designated: Sport

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
123 M/2	6
133 C/5	6-7
713 N/9	7
743	7
923 A/14	6
943 M/13	7
