

# Test Report

Report Number:  
213466-2-TEX



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

Gregersensvej 1  
DK-2630 Taastrup  
+45 72 20 20 00  
info@teknologisk.dk  
www.teknologisk.dk

Page 1 of 4  
Init.: CHF/LELN  
Order no.: 213466  
Encl.: 0

**Assignor:** KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltoft

**Material:** Samples of curtain fabric designated: Vicolo. See page 2 for detailed sample description.

**Sampling:** The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 11 September 2023.

**Period:** The test took place from 12 September 2023 to 10 October 2023.

**Method:** The test methods used are referenced in connection with the results. See page 4.

**Test results:** The results are shown from page 4 onwards.

**Terms:** This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

**Place:** Danish Technological Institute, Taastrup, Environmental Technology

**Signature:** This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.






Charlotte Fischer  
Senior Consultant



**DANAK**  
TEST Reg.no. 2








## Samples

Sample mark	Description	Photo
105	Sample of curtain fabric Designated: Vicolo Composition: 100% Trevira CS	
125	Sample of curtain fabric Designated: Vicolo Composition: 100% Trevira CS	
155	Sample of curtain fabric Designated: Vicolo Composition: 100% Trevira CS	
195	Sample of curtain fabric Designated: Vicolo Composition: 100% Trevira CS	
225	Sample of curtain fabric Designated: Vicolo Composition: 100% Trevira CS	



## Samples (*continued*)

Sample mark	Description	Photo
255	Sample of curtain fabric Designated: Vicolo Composition: 100% Trevira CS	
635	Sample of curtain fabric Designated: Vicolo Composition: 100% Trevira CS	
765	Sample of curtain fabric Designated: Vicolo Composition: 100% Trevira CS	
785	Sample of curtain fabric Designated: Vicolo Composition: 100% Trevira CS	
965	Sample of curtain fabric Designated: Vicolo Composition: 100% Trevira CS	



## Results

### *Test of Samples of curtain fabric designated: Vicolo*

---

#### Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
105	7
125	7
155	6
195	6
225	7
255	6
635	6-7
765	7
785	5-6
965	5-6

---