



Feabrik bv
Mevr. Fatima El Madidi
Minosstraat 20
5048 CK TILBURG
Nederland

Your notice of
 18-01-2019

Your reference

Date
 28-02-2019

Analysis Report 19.00330.02

Required tests :

DIN 4102-1B2 (1998)

Burning behaviour - B2

Identification number	Information given by the client	Date of receipt
T1901361	GENTLE 2 Rust 0373 by Feabrik batch number E-26766006-1	18-01-2019



Gina Créelle
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

Reference: T1901361 - GENTLE 2 Rust 0373 by Febrik batch number E-26766006-1

Burning behaviour - B2

Date of ending the test 20-02-2019
Standard used DIN 4102-1B2 (1998)

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

Ignition Surface- front

Length

	1	2	3	4	5
Time to reach 150 mm mark (s) °	*	*	*	*	*
Ignition filter paper within 20 s after flame application	no	no	no	no	no

° tip of the flame
* = time to reach the mark > 20 s or mark not reached

Width

	1	2	3	4	5
Time to reach 150 mm mark (s) °	*	*	*	*	*
Ignition filter paper within 20 s after flame application	no	no	no	no	no

° tip of the flame
* = time to reach the mark > 20 s or mark not reached

Criteria

- time to reach the mark > 20 s for all test specimens

Conclusion B2