

Müller-BBM GmbH  
Robert-Koch-Str. 11  
82152 Planegg bei München

Telephone +49(89)85602 0  
Telefax +49(89)85602 111

[www.MuellerBBM.de](http://www.MuellerBBM.de)

M. Eng. Philipp Meistring  
Telephone +49(89)85602 228  
[Philipp.Meistring@mbbm.com](mailto:Philipp.Meistring@mbbm.com)

2016-09-22  
M100827/123 MSG/JRE

## **Fabric Floyd Screen Manufacturer Kvadrat A/S**

**Determination of  
airflow resistance according to EN 29053**

**Test Report No. M100827/123**

Client:	Kvadrat A/S Lundbergsvej 10 8400 Ebeltoft DENMARK
Consultant:	M. Eng. Philipp Meistring Jan-Lieven Moll
Date of report:	2016-09-22
Delivery date of test object:	2016-09-22
Date of test:	2016-09-22
Total number of pages:	In total 7 pages: 4 pages text, 1 page Appendix A and 2 pages Appendix B.

Müller-BBM GmbH  
HRB Munich 86143  
VAT Reg. No. DE812167190

Managing directors:  
Joachim Bittner, Walter Grotz,  
Dr. Carl-Christian Hantschk, Dr. Alexander Ropertz,  
Stefan Schierer, Elmar Schröder

## Table of contents

<b>1</b>	<b>Task</b>	<b>3</b>
<b>2</b>	<b>Basics</b>	<b>3</b>
<b>3</b>	<b>Test objects</b>	<b>3</b>
<b>4</b>	<b>Execution of measurements</b>	<b>3</b>
<b>5</b>	<b>Measurement results</b>	<b>4</b>
<b>6</b>	<b>Remarks</b>	<b>4</b>

Appendix A: Measurement results and evaluation

Appendix B: List of test equipment

## 1 Task

On behalf of Kvadrat A/S, 8400 Ebeltoft, Denmark, the airflow resistance of the fabric type Floyd Screen was to be determined according to EN 29053 [1].

## 2 Basics

This test report is based on the following document:

- [1] EN 29053: Acoustics – Materials for acoustical applications – Determination of airflow resistance. 1993

## 3 Test objects

The tested fabric is described in Table 1. The indicated characteristic values were determined by the testing laboratory on the basis of the sample delivered by the manufacturer.

Table 1. Test object.

Test object (manufacturer's information)	Area specific mass $m'$ [g/m <sup>2</sup> ]	Thickness $t$ [mm]
fabric type Floyd Screen, manufacturer Kvadrat A/S material: 50 % polyester, 45 % new wool, 5 % nylon	209	0.47

## 4 Execution of measurements

The airflow resistance was determined according to EN 29053 [1].

The test method, the test facility and the test equipment used are described in Appendix B.

## 5 Measurement results

For the tested fabric type Floyd Screen a specific airflow resistance of

$$R_s = 160 \text{ Pa} \cdot \text{s/m}$$

was determined.

The measurement results are shown in diagrams and tables in the test certificate in Appendix A of this report.

## 6 Remarks

The test results exclusively relate to the investigated subjects and conditions described.



M. Eng. Philipp Meistring  
(Project manager)

This test report may only be published, shown or copied as a whole, including its appendices. The publishing of excerpts is only possible with prior consent of Müller-BBM.



Durch die DAkkS Deutsche Akkreditierungsstelle GmbH  
nach DIN EN ISO/IEC 17025 akkreditiertes Prüflaboratorium.  
Die Akkreditierung gilt für die in der Urkunde aufgeführten Prüfverfahren.

# EN 29053

## Determination of airflow resistance

**Client::** Kvadrat A/S  
 Lundbersvej 10, DK-8400 Ebeltoft

**Project Number::** M100827

**Sample Number::** 12165

**Test object:**  
 - fabric type Floyd Screen  
 - material: 50 % polyester, 45 % new wool, 5 % nylon


Diameter: 100 mm  
 Thickness: 0.47 mm  
 Area-specific mass: 209 g/m<sup>2</sup>

Barometric pressure:  
 $B = 95,7 \text{ kPa}$

Temperature:  
 $\theta = 23,9 \text{ }^\circ\text{C}$

Relative humidity:  
 $r. h. = 31,6 \%$

$u/$ (mm/s)	$R_s/$ (Pa s/m)
4.99	159
6.45	158
7.93	157
9.39	157
10.86	156
12.32	156
13.79	156



Airflow resistance  $R_s = 160 \text{ Pa s/m}$

Laboratory: Planegg  
 Responsible: Moll  
 Date: 2016/09/22

m:\mars 1.2.5738.28997 - \lsmuc-f601\ValleFirmen\MProj\1000\M100827\MarsData\20160922\Floyd Screen.mrs (23.09.2016)

## Description of the test procedure for the determination of the airflow resistance

### 1 Measurand

The specific airflow resistance  $R_S$  of the test object was determined. For this purpose the air pressure difference in front of as well as behind the test object was measured at different volumetric airflow rates. The specific airflow resistance  $R_{S,i}$  for each volumetric airflow rate  $q_i$  determined was calculated using the following equation:

$$R_{S,i} = \frac{\Delta p_i A}{q_i}$$

With

$R_{S,i}$  specific airflow resistance in Pa s/m;

$\Delta p_i$  air pressure difference across the test object with respect to the atmosphere in Pa;

$A$  cross-sectional area of the test object perpendicular to the direction of flow in m<sup>2</sup>;

$q_i$  volumetric airflow rate passing through the test object in m<sup>3</sup>/s;

$u_i$  linear airflow velocity in m/s;

In addition the linear airflow velocity  $u_i$  was determined:

$$u_i = \frac{q_i}{A}$$

The indicated measurement result is the specific airflow resistance  $R_S$ , which is calculated for an airflow velocity of  $u = 0.0005$  m/s by extrapolation with help of the linear regression.

## 2 Test procedure

The direct airflow method (method A according to EN 29053) was applied. A steady unidirectional airflow with different air flow rates is pressed through the test object in the specimen holder. The resulting pressure drop between the two free faces of the test object is measured.

The specimen holder had a diameter of  $D = 100$  mm.

## 3 List of test equipment

The test equipment used is listed in Table B.1.

Table B.1. Test equipment.

Name	Manufacturer	Type	Serial-No.
Measurement system airflow resistance	Müller-BBM	M89319-00	315003
Software for measurement and evaluation	Müller-BBM	m ars	v1.0.0.2
Digital measuring slide	Mitutoyo	CD-15PPR	07019377
Electronic balance	Kern	KB1200-2N	W1402353