

Test Report

Report Number:
202300-6-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 5
Init.: CHF/LELN
Order no.: 202300
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

Material: Samples of upholstery fabric designated: Fiorella. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 15 June 2023.

Period: The test took place from 19 June 2023 to 13 July 2023.

Method: The test methods used are referenced in connection with the results. See page 5.

Test results: The results are shown from page 5 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant







DANAK

TEST Reg.no. 2









Samples

Sample mark	Description	Photo
222 Beige	Sample of Upholstery fabric Designated: Fiorella Composition: 85% polyester, 15% cotton	
222 Brown	Sample of Upholstery fabric Designated: Fiorella Composition: 85% polyester, 15% cotton	
222 White	Sample of Upholstery fabric Designated: Fiorella Composition: 85% polyester, 15% cotton	
192 Black	Sample of Upholstery fabric Designated: Fiorella Composition: 85% polyester, 15% cotton	
192 Grey	Sample of Upholstery fabric Designated: Fiorella Composition: 85% polyester, 15% cotton	
192 White	Sample of Upholstery fabric Designated: Fiorella Composition: 85% polyester, 15% cotton	






Samples (*continued*)

Sample mark	Description	Photo
542 Dark Orange	Sample of Upholstery fabric Designated: Fiorella Composition: 85% polyester, 15% cotton	
542 Light Orange	Sample of Upholstery fabric Designated: Fiorella Composition: 85% polyester, 15% cotton	
542 White	Sample of Upholstery fabric Designated: Fiorella Composition: 85% polyester, 15% cotton	
722 Baby blue	Sample of Upholstery fabric Designated: Fiorella Composition: 85% polyester, 15% cotton	
722 Dark Grey	Sample of Upholstery fabric Designated: Fiorella Composition: 85% polyester, 15% cotton	
722 Light Grey	Sample of Upholstery fabric Designated: Fiorella Composition: 85% polyester, 15% cotton	



Samples (*continued*)

Sample mark	Description	Photo
882 Green	Sample of Upholstery fabric Designated: Fiorella Composition: 85% polyester, 15% cotton	
882 Pink	Sample of Upholstery fabric Designated: Fiorella Composition: 85% polyester, 15% cotton	
882 Light pink	Sample of Upholstery fabric Designated: Fiorella Composition: 85% polyester, 15% cotton	



Results

Test of Samples of upholstery fabric designated: Fiorella

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
222 Beige	6
222 Brown	6
222 White	7
192 Black	4-5
192 Grey	4
192 White	7
542 Dark Orange	4-5
542 Light Orange	5
542 White	6
722 Baby blue	5
722 Dark Grey	6
722 Light Grey	7
882 Green	6
882 Pink	5-6
882 Light pink	6

Test Report

Report Number:
220269-1-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 3
Init.: CHF/LELN
Order no.: 220269
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

Material: Samples of upholstery fabric designated: Fiorella. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 23 November 2023.

Period: The test took place from 24 November 2023 to 21 November 2023.

Method: The test methods used are referenced in connection with the results. See page 3.

Test results: The results are shown from page 3 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant









DANAK

TEST Reg.no. 2



Samples

Sample mark	Description	Photo
192 Black	Samples of upholstery fabric Designated: Fiorella Composition: 68% polyester, 17% recycled polyester, 15% recycled cotton	
192 White	Samples of upholstery fabric Designated: Fiorella Composition: 68% polyester, 17% recycled polyester, 15% recycled cotton	
192 Grey	Samples of upholstery fabric Designated: Fiorella Composition: 68% polyester, 17% recycled polyester, 15% recycled cotton	
542 dark Orange	Samples of upholstery fabric Designated: Fiorella Composition: 68% polyester, 17% recycled polyester, 15% recycled cotton	
542 Orange	Samples of upholstery fabric Designated: Fiorella Composition: 68% polyester, 17% recycled polyester, 15% recycled cotton	
542 White	Samples of upholstery fabric Designated: Fiorella Composition: 68% polyester, 17% recycled polyester, 15% recycled cotton	



Results

Test of Samples of upholstery fabric designated: Fiorella

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
192 Black	5-6
192 White	6
192 Grey	5-6
542 dark Orange	6-7
542 Orange	6-7
542 White	7
