

Test Report

Report Number:
202300-7-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 5
Init.: CHF/LELN
Order no.: 202300
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

Material: Samples of upholstery fabric designated: Keiga. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 15 June 2023.

Period: The test took place from 19 June 2023 to 14 July 2023.

Method: The test methods used are referenced in connection with the results. See page 5.

Test results: The results are shown from page 5 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.







Charlotte Fischer
Senior Consultant



DANAK
TEST Reg.no. 2



Samples

Sample mark	Description	Photo
112	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	
132	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	
142	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	
182	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	
192	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	
222	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	








Samples (*continued*)

Sample mark	Description	Photo
232	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	
242	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	
252	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	
362	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	
382	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	
422	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	



Samples (*continued*)

Sample mark	Description	Photo
572	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	
622	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	
762	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	
822	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	
982	Sample of Upholstery fabricfabric Designated: Keiga Composition: 38% wool, 37% viscose, 16% linen, 9% polyamide	



Results

Test of Samples of upholstery fabric designated: Keiga

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
112	6-7
132	6
142	6
182	6
192	5-6
222	5
232	4
242	6
252	6
362	6
382	6
422	6
572	6-7
622	6-7
762	6-7
822	6-7
982	6

Test Report

Report Number:
225387-1-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 3
Init.: CHF/LELN
Order no.: 225387
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltoft

Material: Sample of upholstery fabric designated: Keiga, 0232. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 20 November 2023.

Period: The test took place from 21 November 2023 to 18 December 2023.

Method: The test methods used are referenced in connection with the results. See page 3.

Test results: The results are shown from page 3 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant



DANAK

TEST Reg.no. 2



Sample

Description: Sample of upholstery fabric

Designated: Keiga, 0232

Composition: 38% new wool, 37% viscose, 16% Flax, 9% nylon

Photo:





Results

Test of Sample of upholstery fabric designated: Keiga, 0232

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Colour fastness
5
