

# Test Report

Report Number:  
204630-1-TEX



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

Gregersensvej 1  
DK-2630 Taastrup  
+45 72 20 20 00  
info@teknologisk.dk  
www.teknologisk.dk

Page 1 of 4  
Init.: CHF/LELN  
Order no.: 204630  
Encl.: 0

**Assignor:** KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

**Material:** Samples of upholstery fabric designated Tablu. See page 2 for detailed sample description.

**Sampling:** The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 4 July 2023.

**Period:** The test took place from 4 July 2023 to 26 July 2023.

**Method:** The test methods used are referenced in connection with the results. See page 4.

**Test results:** The results are shown from page 4 onwards.

**Terms:** This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

**Place:** Danish Technological Institute, Taastrup, Environmental Technology

**Signature:** This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer  
Senior Consultant









**DANAK**

TEST Reg.no. 2






## Samples

Sample mark	Description	Photo
332	Sample of upholstery fabric. Designated: Tablu Fiber content: 67% new wool, 12% linen, 12% viscose, 6% polyester, 3% nylon.	
392	Sample of upholstery fabric. Designated: Tablu Fiber content: 67% new wool, 12% linen, 12% viscose, 6% polyester, 3% nylon.	
482	Sample of upholstery fabric. Designated: Tablu Fiber content: 67% new wool, 12% linen, 12% viscose, 6% polyester, 3% nylon.	
572	Sample of upholstery fabric. Designated: Tablu Fiber content: 67% new wool, 12% linen, 12% viscose, 6% polyester, 3% nylon.	
652	Sample of upholstery fabric. Designated: Tablu Fiber content: 67% new wool, 12% linen, 12% viscose, 6% polyester, 3% nylon.	
142	Sample of upholstery fabric. Designated: Tablu Fiber content: 67% new wool, 12% linen, 12% viscose, 6% polyester, 3% nylon.	



## Samples (*continued*)

Sample mark	Description	Photo
152	Sample of upholstery fabric. Designated: Tablu Fiber content: 67% new wool, 12% linen, 12% viscose, 6% polyester, 3% nylon.	
182	Sample of upholstery fabric. Designated: Tablu Fiber content: 67% new wool, 12% linen, 12% viscose, 6% polyester, 3% nylon.	
232	Sample of upholstery fabric. Designated: Tablu Fiber content: 67% new wool, 12% linen, 12% viscose, 6% polyester, 3% nylon.	



## Results

### *Test of Samples of upholstery fabric designated Tablu*

---

#### Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
332	7
392	7
482	7
572	6-7
652	7
142	7
152	7
182	7
232	7

---