

Test Report

Report Number:
202300-3-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 4
Init.: CHF/LELN
Order no.: 202300
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

Material: Samples of curtain fabric designated: Dadina. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 15 June 2023.

Period: The test took place from 19 June 2023 to 13 July 2023.

Method: The test methods used are referenced in connection with the results. See page 4.

Test results: The results are shown from page 4 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant



DANAK

TEST Reg.no. 2





Samples

Sample mark	Description	Photo
102	Sample of curtain fabric Designated: Dadina Composition: 60% linen, 40% viscose	
142	Sample of curtain fabric Designated: Dadina Composition: 60% linen, 40% viscose	
192	Sample of curtain fabric Designated: Dadina Composition: 60% linen, 40% viscose	
202	Sample of curtain fabric Designated: Dadina Composition: 60% linen, 40% viscose	
222	Sample of curtain fabric Designated: Dadina Composition: 60% linen, 40% viscose	
382	Sample of curtain fabric Designated: Dadina Composition: 60% linen, 40% viscose	



Samples (*continued*)

Sample mark	Description	Photo
712	Sample of curtain fabric Designated: Dadina Composition: 60% linen, 40% viscose	
772	Sample of curtain fabric Designated: Dadina Composition: 60% linen, 40% viscose	



Results

Test of Samples of curtain fabric designated: Dadina

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
102	6
142	7
192	7
202	6
222	5
382	6-7
712	7
772	7
