

Test Report

Report Number:
202300-5-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 5
Init.: CHF/LELN
Order no.: 202300
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltoft

Material: Samples of curtain fabric designated: Phantasia. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 15 June 2023.

Period: The test took place from 19 June 2023 to 13 July 2023.

Method: The test methods used are referenced in connection with the results. See page 5.

Test results: The results are shown from page 5 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant









DANAK

TEST Reg.no. 2



Samples

Sample mark	Description	Photo
462 Branch	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	
462 Yellow	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	
462 Flower	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	
852 Branch	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	
852 Green	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	
852 Flower	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	




Samples (*continued*)

Sample mark	Description	Photo
192 Black	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	
192 Flower	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	
192 Branch	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	
332 Branch	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	
332 Brown	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	
332 Flower	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	



Samples (*continued*)

Sample mark	Description	Photo
112 Branch	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	
112 Beige	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	
112 Flower	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	
132 White flower	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	
132 Beige flower	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	
132 Grey	Sample of curtain fabric Designated: Phantasia Composition: 86% viscose, 14% polyester	



Results

Test of Samples of curtain fabric designated: Phantasia

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
462 Branch	7
462 Yellow	4-5
462 Flower	6-7
852 Branch	7
852 Green	5
852 Flower	6-7
192 Black	4
192 Flower	6
192 Branch	6-7
332 Branch	6
332 Brown	4-5
332 Flower	6-7
112 Branch	6-7
112 Beige	6
112 Flower	6-7
132 White flower	6-7
132 Beige flower	6
132 Grey	4-5
