

Test Report

Report Number:
202300-4-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 6
Init.: CHF/LELN
Order no.: 202300
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

Material: Samples of curtain fabric designated: Gouache. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 15 June 2023.

Period: The test took place from 19 June 2023 to 13 July 2023.

Method: The test methods used are referenced in connection with the results. See page 6.

Test results: The results are shown from page 6 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.







Charlotte Fischer
Senior Consultant



DANAK
TEST Reg.no. 2









Samples

Sample mark	Description	Photo
542 Pink	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
542 Orange	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
542 Yellow	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
642 Pink	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
642 Yellow	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
642 light pink	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	









Samples (*continued*)

Sample mark	Description	Photo
642 Purple	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
742 Blue	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
742 Flower	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
742 Light Blue	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
742 Yellow flower	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
782 Yellow	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	





Samples (*continued*)

Sample mark	Description	Photo
782 Red	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
782 Dark Blue	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
782 Light Blue	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
942 light Green	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
942 dark Green	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
942 Yellow	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	



Samples (*continued*)

Sample mark	Description	Photo
942 White	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
962 Orange	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
962 Red	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
962 dark Green	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	
962 light Green	Sample of curtain fabric Designated: Gouache Composition: 100% polyester	



Results

Test of Samples of curtain fabric designated: Gouache

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
542 Pink	7
542 Orange	6
542 Yellow	6
642 Pink	7
642 light pink	7
642 Yellow	6
642 Purple	5-6
742 Blue	4
742 Flower	7
742 Light Blue	5-6
742 Yellow flower	7
782 Yellow	5
782 Red	4-5
782 Dark Blue	3-4
782 Light Blue	3-4
942 light Green	5
942 dark Green	4-5
942 Yellow	7
942 White	7
962 Orange	6
962 Red	5-6
962 dark Green	3-4
962 light Green	3-4
