

Test Report

Revision 1

Report Number:
190729-10-TEX rev. 1



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 4
Init.: CHF/LELN
Order no.: 190729
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltoft

Material: Samples of curtain fabric designated: Value, item 5512. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 20 April 2023.

Period: The test took place from 21 April 2023 to 17 May 2023.

Method: The test methods used are referenced in connection with the results. See page 4.

Test results: The results are shown from page 4 onwards.

Remarks: This report replaces Report no. 190729-10 of 17.05.2023. Customer wants to have the result entered on sample 230 from report 228378-1, which is a new sample that has been tested.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant









DANAK

TEST Reg.no. 2



Samples

Sample mark	Description	Photo
0100	Sample of curtain fabric Designated: Value Composition: 59% Tencel Luxe, 41% CO organic	
0110	Sample of curtain fabric Designated: Value Composition: 59% Tencel Luxe, 41% CO organic	
0140	Sample of curtain fabric Designated: Value Composition: 59% Tencel Luxe, 41% CO organic	
0170	Sample of curtain fabric Designated: Value Composition: 59% Tencel Luxe, 41% CO organic	
0200	Sample of curtain fabric Designated: Value Composition: 59% Tencel Luxe, 41% CO organic	
0230	Sample of curtain fabric Designated: Value Composition: 59% Tencel Luxe, 41% CO organic	



Samples (continued)

Sample mark	Description	Photo
0220	Sample of curtain fabric Designated: Value Composition: 59% Tencel Luxe, 41% CO organic	
0330	Sample of curtain fabric Designated: Value Composition: 59% Tencel Luxe, 41% CO organic	
0940	Sample of curtain fabric Designated: Value Composition: 59% Tencel Luxe, 41% CO organic	
0950	Sample of curtain fabric Designated: Value Composition: 59% Tencel Luxe, 41% CO organic	



Results

Test of Samples of curtain fabric designated: Value, item 5512

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
0100	6
0110	5-6
0140	4
0170	4
0200	7
0230	4
0220	3
0330	4-5
0940	3-4
0950	5
