

Test Report

Report Number:
216135-1-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 6
Init.: CHF/LELN
Order no.: 216135
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

Material: Samples of upholstery fabric designated: Autumn. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 27 September 2023.

Period: The test took place from 28 September 2023 to 25 October 2023.

Method: The test methods used are referenced in connection with the results. See page 6.

Test results: The results are shown from page 6 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant




DANAK

TEST Reg.no. 2









Samples

Sample mark	Description	Photo
2	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
4	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
7	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
10	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
12	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
13	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	



Samples (*continued*)

Sample mark	Description	Photo
18	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
21	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
23	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
101	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
131	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
171	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	








Samples (*continued*)

Sample mark	Description	Photo
191	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
221	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
331	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
361	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
551	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
651	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	



Samples (*continued*)

Sample mark	Description	Photo
681	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
751	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
771	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
791	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	
971	Sample of upholstery fabric Designated: Autumn Composition: 100% recycled polyester	



Results

Test of Samples of upholstery fabric designated: Autumn

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
2	6-7
4	6-7
7	7
10	7
12	7
13	7
18	7
21	7
23	7
101	7
131	7
171	7
191	7
221	7
331	7
361	7
551	6-7
651	6-7
681	7
751	6-7
771	6-7
791	7
971	7
