Test Report

Report Number: 226638-1-TEX



DANISH TECHNOLOGICAL INSTITUTE

Gregersensvej 1 DK-2630 Taastrup +45 72 20 20 00 info@teknologisk.dk www.teknologisk.dk

Page 1 of 3 Init.: CHF/LELN Order no.: 226638 Encl.: 0

KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltoft	
Samples of curtain fabric designated: Casa Reflect. See page 2 for detailed sample description.	
The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 22 November 2023.	
The test took place from 23 November 2023 to 18 December 2023.	
The test methods used are referenced in connection with the results. See page 3.	
The results are shown from page 3 onwards.	
This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.	
Danish Technological Institute, Taastrup, Environmental Technology	
This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature. Charlotte Fischer Senior Consultant	





Samples

Sample mark	Description	Photo
123	Sample of curtain fabric Designated: Casa Reflect Composition: 100% Trevira CS	
133	Sample of curtain fabric Designated: Casa Reflect Composition: 100% Trevira CS	
213	Sample of curtain fabric Designated: Casa Reflect Composition: 100% Trevira CS	
233	Sample of curtain fabric Designated: Casa Reflect Composition: 100% Trevira CS	
183	Sample of curtain fabric Designated: Casa Reflect Composition: 100% Trevira CS	



Results

Test of Samples of curtain fabric designated: Casa Reflect

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2 1-8 scale, 8 best rating Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
123	7
133	7
213	7
233	7
183	7