

Test Report

Report Number:
177778-1-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 4
Init.: CHF/LELN
Order no.: 177778
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltoft

Material: Samples of upholstery fabric designated: Serpentine. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 30 January 2023.

Period: The test took place from 30 January 2023 to 17 February 2023.

Method: The test methods used are referenced in connection with the results. See page 4.

Test results: The results are shown from page 4 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.







Charlotte Fischer
Senior Consultant



DANAK
TEST Reg.no. 2



Samples

| Sample mark | Description | Photo |
|-------------|---|---|
| 798 | Samples of upholstery fabric Designated: Serpentine Fibre content: 98% new wool, 2% nylon |  |
| 118 | Samples of upholstery fabric Designated: Serpentine Fibre content: 98% new wool, 2% nylon |  |
| 158 | Samples of upholstery fabric Designated: Serpentine Fibre content: 98% new wool, 2% nylon |  |
| 198 | Samples of upholstery fabric Designated: Serpentine Fibre content: 98% new wool, 2% nylon |  |
| 358 | Samples of upholstery fabric Designated: Serpentine Fibre content: 98% new wool, 2% nylon |  |
| 238 | Samples of upholstery fabric Designated: Serpentine Fibre content: 98% new wool, 2% nylon |  |



Samples (*continued*)

| Sample mark | Description | Photo |
|-------------|---|---|
| 438 | Samples of upholstery fabric Designated: Serpentine Fibre content: 98% new wool, 2% nylon |  |
| 428 | Samples of upholstery fabric Designated: Serpentine Fibre content: 98% new wool, 2% nylon |  |
| 498 | Samples of upholstery fabric Designated: Serpentine Fibre content: 98% new wool, 2% nylon |  |
| 928 | Samples of upholstery fabric Designated: Serpentine Fibre content: 98% new wool, 2% nylon |  |
| 988 | Samples of upholstery fabric Designated: Serpentine Fibre content: 98% new wool, 2% nylon |  |
| 678 | Samples of upholstery fabric Designated: Serpentine Fibre content: 98% new wool, 2% nylon |  |



Results

Test of Samples of upholstery fabric designated: Serpentine

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

| Sample mark | Colour fastness |
|-------------|-----------------|
| 798 | 5-6 |
| 118 | 6-7 |
| 158 | 5-6 |
| 198 | 6 |
| 358 | 6 |
| 238 | 6 |
| 438 | 6-7 |
| 428 | 7 |
| 498 | 6-7 |
| 928 | 6-7 |
| 988 | 6 |
| 678 | 6-7 |
