



Confidential Report

Our Ref: 23/61321B2/08/23





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 30 August 2023

Our Ref: 23/61321B2/08/23

Your Ref: ---

Page: 1 of 5

Client:

Kvadrat A/S

Lundbergsvej 10
8400 Ebeltoft
Denmark

Job Title:

Fire Test on One Fabric Sample

Clients Order Ref:

--

Date of Receipt:

21 August 2023

Date Test Started:

25 August 2023

Description of Sample:

One sample of fabric, which was referenced by the client as;

Keiga

Stated to be: 38% New Wool, 37% Viscose, 16% Linen, 9% Nylon

Work Requested:

We were asked to make the following fire test:

BS 7176: 2007 + A1:2011 (Low Hazard)

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited



1066

Note: This report relates only to the items tested.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG® and Shirley® are trade names of Shirley Technologies Ltd.

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2023 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 30 August 2023

Our Ref: 23/61321B2/08/23

Your Ref: ---

Page: 2 of 5

Client: Kvadrat A/S

Specification BS 7176: 2007 + A1:2011 Resistance to Ignition of Upholstered Furniture for non-domestic seating by testing composites using BS EN 1021:2006 Furniture – Assessment of the ignitability of upholstered furniture Parts 1 and 2 (Low Hazard).

Pre-Treatment

The material received no pre-treatment as the fabric is stated not to be FR treated.

Conditioning

The materials for testing to Source 0 and 1 were conditioned for a minimum of 24 hours and tested in the environments specified in Clause 7 of BS EN 1021-1 & 2:2006.

Foam Used

The sample was tested over Non FR polyurethane foam with a density of approximately 20-22kg/m³.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2023 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
 Telephone: +44 (0) 113 259 1999
 Email: onestopshop@bttg.co.uk
 Website: www.bttg.co.uk

Date: 30 August 2023

Our Ref: 23/61321B2/08/23

Your Ref: ---

Page: 3 of 5

Client: **Kvadrat A/S**

Testing to BS EN 1021-1:2006 – Source 0 – Cigarette

The sample was tested in accordance with BS EN 1021-1:2006.

The test results relate only to the ignitability of the combustion of upholstery composites under the particular conditions of test stated, they are not intended as a means of assessing the full potential fire hazard of the materials of products in use.

Results

Smouldering criteria	Specimen No.	
	1	2
Unsafe escalating combustion	No	No
Testing assembly consumed	No	No
Smoulders to extremities/full thickness	No	No
Smoulders more than 1 hour	No	No
In final examination, presence of progressive smouldering	No	No

Flaming criteria	1	2
Occurrence of flames	No	No
Specimen Result (Ignition or Non-ignition)	Non-Ignition (NI)	Non-Ignition (NI)

Any “Yes” in smouldering or flaming criteria means Ignition

Cigarette Test Result PASS





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
 Telephone: +44 (0) 113 259 1999
 Email: onestopshop@bttg.co.uk
 Website: www.bttg.co.uk

Date: 30 August 2023

Our Ref: 23/61321B2/08/23

Your Ref: ---

Page: 4 of 5

Client: **Kvadrat A/S**

BS EN 1021-2: 2006 – Source 1 – Butane Flame (Match)

The sample was tested in accordance with BS EN 1021-2:2006.

The test results relate only to the ignitability of the combustion of upholstery composites under the particular conditions of test stated, they are not intended as a means of assessing the full potential fire hazard of the materials of products in use.

Results

	Specimen No.	
	1	2
Smouldering criteria		
Unsafe escalating combustion	No	No
Testing assembly consumed	No	No
Smoulders to extremities/full thickness	No	No
Smoulders more than 1 hour	No	No
In final examination, presence of progressive smouldering	No	No
Flaming criteria		
Unsafe escalating combustion	No	No
Testing assembly consumed	No	No
Flames to extremities/full thickness	No	No
Flames longer than 120 seconds	No	No
Specimen Result		
Ignition (I) / Non Ignition (NI)	NI	NI

Any "Yes" in smouldering or flaming criteria means Ignition

Match Test Result PASS





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 30 August 2023

Our Ref: 23/61321B2/08/23
Your Ref: ---

Page: 5 of 5

Client: **Kvadrat A/S**

Conclusion

The combination of materials meets BS 7176:2007+A1:2011 for Low Hazard.

See BS 7176: 2007 + A1: 2011 Clause 6 for labelling and identification requirements. The test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test stated (BS EN 1021-1: 2006, BS EN 1021-2: 2006 and BS 5852: 2006 respectively); they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (<https://www.bttg.co.uk/about-us/decision-rules-policy/>) for further information.

Uncertainty Budget

Measurements: $\pm 2\text{mm}$
Timings: ± 2 seconds.

Reported by:..... R Greasley, Laboratory Technician

Countersigned by:..... B Bland, Technical Customer Service Officer

Enquiries concerning this report should be addressed to Customer Services.

