Test Report

Report Number: 133334-16-TEX



DANISH TECHNOLOGICAL

INSTITUTE

Gregersensvej 1 DK-2630 Taastrup +45 72 20 20 00 info@teknologisk.dk www.teknologisk.dk

Page 1 of 4 Init.: CHF/LELN Order no.: 133334

Encl.: 0

Assignor: KINNASAND GMBH, Danziger Strasse 6, D-26655 Westerstede, Germany

Material: Sample of fabrics designated: Shutter 7118. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the

assignor and received at Danish Technological Institute on 17 May 2022.

Period: The test took place from 18 May 2022 to 10 June 2022.

Method: The test methods used are referenced in connection with the results. See page 4.

Test results: The results are shown from page 4 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC

17025:2017) and in accordance with the General Terms and Conditions of Danish

Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The

date of issue appears from the digital signature.

Charlotte Fischer Senior Consultant









Samples

Sample mark	Description	Photo
Col. 0006	Sample of fabric Designated: Shutter, 7118	
Col. 0001	Sample of fabric Designated: Shutter, 7118	
Col. 0016	Sample of fabric Designated: Shutter, 7118	
Col. 0023	Sample of fabric Designated: Shutter, 7118	
Col. 0024	Sample of fabric Designated: Shutter, 7118	
Col. 0012	Sample of fabric Designated: Shutter, 7118	

133334-16-TEX Page 2 of 4



Samples (continued)

Sample mark	Description	Photo
Col. 0015	Sample of fabric Designated: Shutter, 7118	
Col. 0026	Sample of fabric Designated: Shutter, 7118	
Col. 0013	Sample of fabric Designated: Shutter, 7118	
Col. 0033	Sample of fabric Designated: Shutter, 7118	

133334-16-TEX Page 3 of 4



Results

Test of Sample of fabrics designated: Shutter 7118

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
Col. 0006	5
Col. 0001	7
Col. 0016	4
Col. 0023	5-6
Col. 0024	4-5
Col. 0012	5
Col. 0015	5
Col. 0026	3-4
Col. 0013	5
Col. 0033	4

133334-16-TEX Page 4 of 4