

Test Report

Report No.: A 884227-1



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk

Assignor: Kinnasand GmbH
Danziger Strasse 6
26655 Westerstede
Germany
Attn.: Sonja Fröhlich

Page 1 of 1
Chf/leln
Order no.: 884227
No. of appendices: 1

Subject: Curtain fabric Art. Dive 6994 (as per info from the assignor).

Sampling: The test material was sampled by the client and received at the Danish Technological Institute 15.08.2019

Method: See Appendix 1.

Period: The testing was completed 09.09.2019

Result: Individual results appear from Appendix 1.

Storage: The test material will be destroyed after 6 months, unless otherwise agreed.

Terms: The accredited test was carried out according to DANAK's general conditions see www.danak.dk and according to the General Terms and Conditions regarding Commissioned Work Accepted by the Danish Technological Institute, which apply at the time of signing the agreement. The test is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

Date/place: 11.09.2019, Danish Technological Institute, Wood and Biomaterials, Textile, Taastrup

Charlotte Fischer

Charlotte Fischer
Ph. Direct: +45 72 20 21 35
E-mail: charlotte.fischer@teknologisk.dk

Lea Larsen

Lea Larsen
Ph. Direct: +45 72 20 21 35
E-mail: lea@teknologisk.dk

Signature: Test responsible

Co-signatory



Report no.: A 884227-1
 Appendix: 1
 Page: 1 of 1
 Initials: Chf/leln

Test Methods	Results
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	0001 Colour fastness: 7
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	0011 Colour fastness: 7
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	0013 Colour fastness: 6
Colour fastness to artificial light DS/EN ISO 105:B02:2014 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	0016 Colour fastness: 5

Test Report

Report Number:
108178-13-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 4
Init.: CHF/LELN
Order no.: 108178
Encl.: 0

Assignor: Kinnasand GmbH, Danziger Strasse 6 , D-26655 Westerstede, Germany

Material: Sample of curtain fabric designated: Dive. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 9 November 2021.

Period: The test took place from 10 November 2021 to 7 December 2021.

Method: The test methods used are referenced in connection with the results. See page 4.

Test results: The results are shown on page 4.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant



DIGITALLY SIGNED DOCUMENT

8 December 2021

DANISH TECHNOLOGICAL INSTITUTE



DANAK

TEST Reg.no. 2







Samples

Sample mark	Description	Photo
Col. 0002	Sample of fabric Designated: Dive	
Col. 0010	Sample of fabric Designated: Dive	
Col. 0006	Sample of fabric Designated: Dive	
Col. 0004	Sample of fabric Designated: Dive	
Col. 0015	Sample of fabric Designated: Dive	



Samples (*continued*)

Sample mark	Description	Photo
Col. 0024	Sample of fabric Designated: Dive	
Col. 0021	Sample of fabric Designated: Dive	
Col. 0022	Sample of fabric Designated: Dive	
Col. 0014	Sample of fabric Designated: Dive	



Results

Test of Sample of curtain fabric designated: Dive

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
Col. 0002	7
Col. 0010	7
Col. 0006	6
Col. 0004	7
Col. 0015	6-7
Col. 0024	5
Col. 0021	5-6
Col. 0022	5-6
Col. 0014	6
