



# Test Report

Report No.: A 846517-3

**Assignor:** Kvadrat A/S  
Lundbergsvej 10  
8400 Ebeltoft  
Attn.: Lone Henriksen

Page 1 of 2  
Initials CHF/LeIn  
Order no.: 846517  
No. of appendix: 1

**Subject:** Combination of upholstered material tested:  
**Cover:** Sample of upholstery fabric, designated: Atom  
Fibre composition: 90% new wool, 8% nylon, 2% polyester worsted (as per info from the assigner)  
Approximate mass per area unit: 732 g/m<sup>2</sup>.  
**Filling:** Polyurethane foam, specified in TB 117-2013 Annex B  
Density 28,0 - 29,6 kg/m<sup>3</sup>.  
(Foam was submitted by Danish Technological Institute)

**Sampling:** The test material was sampled by the client and received at the Danish Technological Institute 7 December 2018.

**Method:** California Bureau of Home Furnishings and Thermal Insulation Technical Bulletin 117-2013. Section 1. Cover fabric test.

**Period:** The testing was completed 12 December 2018.

**Result:** The cover fabric under test **meets (PASSES)** the requirements to flammability of cover fabrics specified in Technical Bulletin 117-2013, Section 1 from Bureau of Home Furnishings and Thermal Insulation, State of California, USA.

Details of the tests are given on pages 2 of this report.

**Storage:** The test material will be destroyed after 3 months, unless otherwise agreed.

**Terms:** Accredited testing was carried out in compliance with international requirements (EN/ISO/IEC 17025:2005) and in compliance with Danish Technological Institute's General Terms and Conditions regarding Commissioned Work accepted by Danish Technological Institute. The test results apply to the tested products only. This report may be quoted in extract only if the laboratory has granted its written consent.

**Date/place:** 14 December 2018, Danish Technological Institute, Textile, Taastrup

**Signature:** Test responsible

Co-signatory



Report no.: A 846517-3  
Page: 2 of 2  
Initials: CHF/LeIn

**Results,  
continued:**

Testing according to Technical Bulletin 117-2013, Section 1

Smouldering test (cigarette test) for cover fabric materials in combination with standard polyurethane foam, specified in TB 117-2013 Annex B. Test materials were conditioned at 21±2 °C (70±5 °F) and less than 55 % RH. A fresh cigarette must be placed on new a test assembly, until either three cigarettes have burned their entire length on three individual test specimens, or three cigarettes have self-extinguished on the specimen.

Three determinations were carried out:

	Test 1	Test 2	Test 3
Smouldering after 45 minutes	*No	*No	*No
Vertical char length in inches	0,24 (6 mm)	0,31 (8 mm)	0,20 (5 mm)
Cigarette burned entire length	No	No	No
Occurrence of flames	No	No	No
Comments: *Cigarettes self-extinguished			

**Requirements:**

A material is considered to pass or fail based on the following criteria according to Technical Bulletin 117-2013, Section 1, item 3.4:

1.	A single mock-up test specimen fails to meets the requirements of this test procedure if any of the following criteria occurs:
	a) The mock-up test specimen continues to smoulder after 45 minutes test duration.
	b) A vertical char length of more than 1,8 inches (45 mm) develops on the cover fabric.
	c) The mock-up test specimen transitions to open flame.
2.	The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn full length and the mock-ups are no longer smouldering.
3.	If more than one initial specimen fails, the cover fabric fails the test.
4.	If any of the three initial specimen fails, repeat the test on additional three specimens.
5.	If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.



Report no.: A 846517-3  
Appendix: 1  
Page: 1 of 1  
Initials: CHF/Leln

