

Test Report

Report Number:
256805-1-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 8
Init.: CHF/LELN
Order no.: 256805
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

Material: Samples of curtain fabric designated: Time recycled, item:1043. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 13 May 2024.

Period: The test took place from 14 May 2024 to 14 June 2024.

Method: The test methods used are referenced in connection with the results. See page 8.

Test results: The results are shown from page 8 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant








DANAK

TEST Reg.no. 2



Samples

Sample mark	Description	Photo
0104	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0114	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0134	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0184	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0204	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	



Samples *(continued)*



Sample mark	Description	Photo
0214	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0224	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0234	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0244	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0254	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0394	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0434	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	





Samples (continued)

Sample mark	Description	Photo
0504	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0534	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0574	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0644	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0724	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0754	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	



Samples (continued)

Sample mark	Description	Photo
0784	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0854	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0924	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	
0954	Sample of curtain fabric Designated: Time recycled, item:1043 Composition: 95% REC PES FR, 5% PES FR	



Results

Test of Samples of curtain fabric designated: Time recycled, item:1043

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
0104	6-7
0114	7
0134	7
0184	7
0204	7
0214	7
0224	7
0234	6-7
0244	6-7
0254	6
0394	6
0434	7
0504	6-7
0534	6-7
0574	6
0644	6
0724	6-7
0754	6-7
0784	6-7
0854	6-7
0924	6-7
0954	6-7
