

Test Report

Report Number:
226321-1-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 4
Init.: CHF/LELN
Order no.: 226321
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltoft

Material: Samples of fabric designated: Ame. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 22 November 2023.

Period: The test took place from 22 November 2023 to 18 December 2023.

Method: The test methods used are referenced in connection with the results. See page 4.

Test results: The results are shown from page 4 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant







DANAK

TEST Reg.no. 2










Samples

Sample mark	Description	Photo
112	Sample of fabric Designated: Ame Composition: 100% polyester	
122	Sample of fabric Designated: Ame Composition: 100% polyester	
172	Sample of fabric Designated: Ame Composition: 100% polyester	
192	Sample of fabric Designated: Ame Composition: 100% polyester	
222	Sample of fabric Designated: Ame Composition: 100% polyester	
242	Sample of fabric Designated: Ame Composition: 100% polyester	



Samples (*continued*)

Sample mark	Description	Photo
342	Sample of fabric Designated: Ame Composition: 100% polyester	
482	Sample of fabric Designated: Ame Composition: 100% polyester	
742	Sample of fabric Designated: Ame Composition: 100% polyester	
782	Sample of fabric Designated: Ame Composition: 100% polyester	
962	Sample of fabric Designated: Ame Composition: 100% polyester	
982	Sample of fabric Designated: Ame Composition: 100% polyester	
992	Sample of fabric Designated: Ame Composition: 100% polyester	



Results

Test of Samples of fabric designated: Ame

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
112	7
122	7
172	7
192	6
222	7
242	7
342	7
482	6
742	6
782	6
962	6-7
982	6
992	6
