

kvadrat

Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft Denmark
T +45 89 53 18 66 F +45 89 53 18 00
www.kvadrat.dk kvadrat@kvadrat.dk

CVR 45998517 Jyske Bank 5073 117977-1

Fastness to rubbing ISO 105-X12

Ame

Colour number	Dry condition	Wet Condition
112	5	5
122	5	4-5
172	4-5	4-5
192*	4-5	4-5
222	5	5
242	5	5
342	5	4-5
482	4-5	4-5
742	4-5	4-5
782*	4-5	4-5
962	4-5	4-5
982	4-5	4-5

Danish Technological Institute – 265337-1-TEX, 4. July 2024
Internal test LH/lh 2024.07.02

Test Report

Report Number:
265337-1-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 3
Init.: CHF/LELN
Order no.: 265337
Encl.: 0

Assignor: KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

Material: Samples of upholstery fabric designated: Ame. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 1 July 2024.

Period: The test took place from 2 July 2024 to 3 July 2024.

Method: The test methods used are referenced in connection with the results. See page 3.

Test results: The results are shown from page 3 onwards.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant





DANAK

TEST Reg.no. 2



Samples

Sample mark	Description	Photo
0192	Sample of upholstery fabric Designated: Amecomposition: 100% polyester (recycled textile waste)	
0782	Sample of upholstery fabric Designated: Amecomposition: 100% polyester (recycled textile waste)	



Results

Test of Samples of upholstery fabric designated: Ame

Colour fastness to rubbing

EN ISO 105-X12:2016
1-5 scale, 5 best rating

Test conditions: 21°C, 65% RH
Rubbing finger: Cylinder 16 mm

Conditioning time: 24 h
Force: 9 N

Soak: 100%

Staining Sample	Warp direction		Weft direction	
	Dry rubbing	Wet rubbing	Dry rubbing	Wet rubbing
0192	4-5	4-5	4-5	4-5
0782	4-5	4-5	4-5	4-5
