

# Test Report

Report Number:  
133334-6-TEX



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

Gregersensvej 1  
DK-2630 Taastrup  
+45 72 20 20 00  
info@teknologisk.dk  
www.teknologisk.dk

Page 1 of 3  
Init.: CHF/LELN  
Order no.: 133334  
Encl.: 0

**Assignor:** KINNASAND GMBH, Danziger Strasse 6 , D-26655 Westerstede, Germany

**Material:** Sample of fabrics designated: **Untitled AB 5, 7116**. See page 2 for detailed sample description.

**Sampling:** The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 7 April 2022.

**Period:** The test took place from 8 April 2022 to 5 May 2022.

**Method:** The test methods used are referenced in connection with the results. See page 3.

**Test results:** The results are shown on page 3.

**Terms:** This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

**Place:** Danish Technological Institute, Taastrup, Environmental Technology

**Signature:** This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.  
  
Charlotte Fischer  
Senior Consultant



DIGITALLY SIGNED DOCUMENT

5 May 2022

DANISH TECHNOLOGICAL INSTITUTE



**DANAK**

TEST Reg.no. 2



## Samples

Sample mark	Description	Photo
Col. 0013 Dark grey	Sample of fabric Designated: Untitled AB 5, 7116	
Col. 0001 White	Sample of fabric Designated: Untitled AB 5, 7116	
Col. 0033 Dark grey	Sample of fabric Designated: Untitled AB 5, 7116	
Col. 0033 Light Grey	Sample of fabric Designated: Untitled AB 5, 7116	
Col. 0026 Dark Grey	Sample of fabric Designated: Untitled AB 5, 7116	
Col. 0026 Light Grey	Sample of fabric Designated: Untitled AB 5, 7116	
Col. 0013 Light Grey	Sample of fabric Designated: Untitled AB 5, 7116	



## Results

### *Test of Sample of fabrics designated: Untitled AB 5, 7116*

---

#### Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
Col. 0013 Dark grey	6-7
<i>COL. 0001</i>	6-7
Col. 0033 Dark grey	3-4
Col. 0033 Light Grey	6
Col. 0026 Dark Grey	7
Col. 0026 Light Grey	6
Col. 0013 Light Grey	6-7

---