

Test Report

Report Number:
133334-10-TEX



**DANISH
TECHNOLOGICAL
INSTITUTE**

Gregersensvej 1
DK-2630 Taastrup
+45 72 20 20 00
info@teknologisk.dk
www.teknologisk.dk

Page 1 of 4
Init.: CHF/LELN
Order no.: 133334
Encl.: 0

Assignor: KINNASAND GMBH, Danziger Strasse 6 , D-26655 Westerstede, Germany

Material: Samples of fabric designated: Untitled AB 6. See page 2 for detailed sample description.

Sampling: The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 29 April 2022.

Period: The test took place from 2 May 2022 to 23 May 2022.

Method: The test methods used are referenced in connection with the results. See page 4.

Test results: The results are shown on page 4.

Terms: This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

Place: Danish Technological Institute, Taastrup, Environmental Technology

Signature: This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer
Senior Consultant



DIGITALLY SIGNED DOCUMENT

23 May 2022

DANISH TECHNOLOGICAL INSTITUTE









DANAK

TEST Reg.no. 2







Samples

Sample mark	Description	Photo
0001 White fabric	Sample of fabric Designated: Untitled AB 6	
0001 Black fabric	Sample of fabric Designated: Untitled AB 6	
0003 Beige fabric	Sample of fabric Designated: Untitled AB 6	
0003 Black fabric	Sample of fabric Designated: Untitled AB 6	
0016 Grey fabric	Sample of fabric Designated: Untitled AB 6	
0016 Black fabric	Sample of fabric Designated: Untitled AB 6	



Samples (continued)

Sample mark	Description	Photo
0024 Beige fabric	Sample of fabric Designated: Untitled AB 6	
0024 Black fabric	Sample of fabric Designated: Untitled AB 6	
0033 Grey fabric	Sample of fabric Designated: Untitled AB 6	
0033 Black fabric	Sample of fabric Designated: Untitled AB 6	



Results

Test of Samples of fabric designated: Untitled AB 6

Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
0001 White fabric	6
0001 Black fabric	7
0003 Beige fabric	6
0003 Black fabric	7
0016 Grey fabric	5-6
0016 Black fabric	7
0024 Beige fabric	6
0024 Black fabric	7
0033 Grey fabric	4
0033 Black fabric	7
