

Module - Fabric Tensile**Standard - EN ISO 13936-2 (180N)**

Date

April 2004

Title Determination of the slippage resistance of yarns at a seam in woven fabrics

Jaw Separation 100,00mm

Pretension

0,00N

Break Detection 0,00%

Profile 1 of 3

Rate of Extension 50mm/min

Maximum Load

180,00N

Time at Max Load

Profile 2 of 3

Rate of Extension 50mm/min

Maximum Load

5,00N

Time at Max Load

Profile 3 of 3

Rate of Extension 50mm/min

Maximum Load

5,00N

Time at Max Load

Specimens 3

Warp & Weft

Jaws Scheme T17

T17 top T17 bottom (plain jaw faces)

Customer - Sahco**Test - Coney**

Reference

600147

Material 43% viscose, 29% polyester, 15% nylon, 13% cotton

User Name

Load Cell S/N

3000N 677174

Date

08-11-2024

Machine S/N

910/12/1084

Time

15:00:49

Version


9.4.0.24789

Licensed for use by

KVADRAT AS

Machine Type

Titan - Universal Strength Tester by James H. Heal & Co. Ltd.



Results - Warp Over Weft

Specimen	Seam Opening	Observations
1	mm	
2	1,00	
3	1,00	
Statistics		
Mean	1,00	

Module - Fabric Tensile**Standard - EN ISO 13936-2 (180N)**


Title	Determination of the slippage resistance of yarns at a seam in woven fabrics	Date	April 2004
Jaw Separation	100,00mm	Pretension	0,00N
Break Detection	0,00%		
Profile 1 of 3			
Rate of Extension	50mm/min	Maximum Load	180,00N
Time at Max Load			
Profile 2 of 3			
Rate of Extension	50mm/min	Maximum Load	5,00N
Time at Max Load			
Profile 3 of 3			
Rate of Extension	50mm/min	Maximum Load	5,00N
Time at Max Load			
Specimens	3	Warp & Weft	
Jaws Scheme	T17	T17 top T17 bottom (plain jaw faces)	

Customer - Sahco**Test - Coney**

Material	43% viscose, 29% polyester, 15% nylon, 13% cotton	Reference	600147
----------	---	-----------	--------

User Name

Load Cell S/N	3000N 677174	Date	08-11-2024
Machine S/N	910/12/1084	Time	15:00:49
Version	9.4.0.24789		
Licensed for use by	KVADRAT AS		
Machine Type	Titan - Universal Strength Tester by James H. Heal & Co. Ltd.		



Results - Weft Over Warp

Specimen	Seam Opening	Observations
1	mm	
2	1,00	
3	1,00	
Statistics		
Mean	1,00	