

# Test Report

Report Number:  
259972-3-TEX



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

Gregersensvej 1  
DK-2630 Taastrup  
+45 72 20 20 00  
info@teknologisk.dk  
www.teknologisk.dk

Page 1 of 3  
Init.: CHF/LELN  
Order no.: 259972  
Encl.: 0

**Assignor:** KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

**Material:** Sample of curtain fabric designated: Ozi. See page 2 for detailed sample description.

**Sampling:** The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 3 June 2024.

**Period:** The test took place from 4 June 2024 to 25 June 2024.

**Method:** The test methods used are referenced in connection with the results. See page 3.

**Test results:** The results are shown from page 3 onwards.

**Terms:** This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

**Place:** Danish Technological Institute, Taastrup, Environmental Technology

**Signature:** This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.  
  
Charlotte Fischer  
Senior Consultant



**DANAK**  
TEST Reg.no. 2



## Samples

Sample mark	Description	Photo
110	Sample of curtain fabric Designated: Ozi Composition: 24% PA, 76% PES rec	
180	Sample of curtain fabric Designated: Ozi Composition: 24% PA, 76% PES rec	
220	Sample of curtain fabric Designated: Ozi Composition: 24% PA, 76% PES rec	
580	Sample of curtain fabric Designated: Ozi Composition: 24% PA, 76% PES rec	
670	Sample of curtain fabric Designated: Ozi Composition: 24% PA, 76% PES rec	
730	Sample of curtain fabric Designated: Ozi Composition: 24% PA, 76% PES rec	
960	Sample of curtain fabric Designated: Ozi Composition: 24% PA, 76% PES rec	



## Results

### *Test of Sample of curtain fabric designated: Ozi*

---

#### Colour fastness to artificial light: Xenon arc fading lamp test

EN ISO 105-B02:2014 Method 2

1-8 scale, 8 best rating

Test apparatus: Atlas Ci4000 Xenon Weather-Ometer

Sample mark	Colour fastness
110	7
180	6
220	7
580	5-6
670	7
730	7
960	7

---