

# Test Report

Report Number:  
263403-1-TEX



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

Gregersensvej 1  
DK-2630 Taastrup  
+45 72 20 20 00  
info@teknologisk.dk  
www.teknologisk.dk

Page 1 of 3  
Init.: CHF/LELN  
Order no.: 263403  
Encl.: 0

<b>Assignor:</b>	KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft
<b>Material:</b>	Sample of upholstery fabric designated: Coda 2, 103. See page 2 for detailed sample description.
<b>Sampling:</b>	The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 18 June 2024.
<b>Period:</b>	The test took place from 19 June 2024 to 24 June 2024.
<b>Method:</b>	The test methods used are referenced in connection with the results. See page 3.
<b>Test results:</b>	The results are shown from page 3 onwards.
<b>Terms:</b>	This test was conducted in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.
<b>Place:</b>	Danish Technological Institute, Taastrup, Environmental Technology
<b>Signature:</b>	This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.  Charlotte Fischer Senior Consultant



## Sample

Description: Sample of upholstery fabric  
Designated: Coda 2, 103  
Composition: 90% new wool, 10% nylon

Photo:





## Results

### *Test of Sample of upholstery fabric designated: Coda 2, 103*

---

#### Determination of fabric propensity to surface snagging\*

ICI Test method FAB 29. Tumble-Box (1 steel spike in each box face) Test conditions: 21°C, 65% RH  
1-4 scale, 1 best rating. The sample is rated by comparison with photos of four standard fabrics.  
Standard 1: Very satisfactory. Standard 2: Acceptable. Standard 3: Doubtful. Standard 4: Unacceptable.

Pre-treatment	Test parameters	Results
(none)	Number of test specimens: 4 Number of observers: 2 Number of revolutions: 18000	Final grade: 1

\*) Not covered by the accreditation reg. no. 2

---