

# Test Report

Report Number:  
237383-1-TEX



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

Gregersensvej 1  
DK-2630 Taastrup  
+45 72 20 20 00  
info@teknologisk.dk  
www.teknologisk.dk

Page 1 of 4  
Init.: CHF/LELN  
Order no.: 237383  
Encl.: 0

**Assignor:** KVADRAT A/S, Lundbergsvej 10, DK-8400 Ebeltøft

**Material:** Sample of upholstery fabric designated: Zade. See page 2 for detailed sample description.

**Sampling:** The assignor confirms having selected the product. The product was forwarded by the assignor and received at Danish Technological Institute on 25 January 2024.

**Period:** The test took place from 26 January 2024 to 31 January 2024.

**Method:** The test methods used are referenced in connection with the results. See page 3.

**Test results:** The results are shown from page 3 onwards.

**Terms:** This test was conducted accredited in accordance with international requirements (ISO/IEC 17025:2017) and in accordance with the General Terms and Conditions of Danish Technological Institute. The test results solely apply to the tested item. This test report may be quoted in extract only if Danish Technological Institute has granted its written consent.

**Place:** Danish Technological Institute, Taastrup, Environmental Technology

**Signature:** This document is only valid with a digital signature from Danish Technological Institute. The date of issue appears from the digital signature.

Charlotte Fischer  
Senior Consultant



**DANAK**

TEST Reg.no. 2



## Samples

Sample mark	Description	Photo
1	<p>Sample of upholstery fabric Designated Zade Composition: 56% Viscose, 25% cotton, 19% polyester Approximate mass per area: 779 g/m<sup>2</sup></p>	



## Results

### *Test of Sample of upholstery fabric designated: Zade*

#### Determination of the abrasion resistance of fabrics by the Martindale method

##### Part 2: Determination of specimen breakdown

EN ISO 12947-2:2016

Test conditions: 21°C, 65% RH

Colour change: DS EN 20105-A02:1997:1997 (1-5 scale, 5 best rating)

Sample	Pre-treatment	Test parameters	Results [rubs]
1	(none)	Mass: 795 g Nominal pressure: 12 kPa End-point: Two broken threads	40000 35000 40000  End result: 35000 Colour change: Note 3-4 after 6000 rubs

#### Determination of fabric propensity to surface pilling, fuzzing and matting

##### Part 2: Modified Martindale method

EN ISO 12945-2:2020

1-5 scale, 5 best rating

Test conditions: 21°C, 65% RH

Evaluation: EN ISO 12945-4:2020

Sample	Pre-treatment	Test parameters	Results							
			Property	Specimen	125	500	1000	2000	500	7000
1	(none)	Number of test specimens: 3 Number of observers: 2 Abradant: Wool abradant fabric Loading mass: 415 g	Number of revolutions							
			Pilling	1	5	5	5	5	5	5
				2	5	5	5	5	5	5
				3	5	5	5	5	5	5
				Average	5	5	5	5	5	5
			Fuzzing	1	3-4	3-4	3-4	3	3	3
				2	3-4	3-4	3-4	3	3	3
				3	3-4	3-4	3-4	3	3	3
				Average	3-4	3-4	3-4	3	3	3



### Determination of fabric propensity to surface snagging\*

ICI Test method FAB 29. Tumble-Box (1 steel spike in each box face) Test conditions: 21°C, 65% RH  
1-4 scale, 1 best rating. The sample is rated by comparison with photos of four standard fabrics.  
Standard 1: Very satisfactory. Standard 2: Acceptable. Standard 3: Doubtful. Standard 4: Unacceptable.

Sample	Pre-treatment	Test parameters	Results
1	(none)	Number of test specimens: 4 Number of observers: 2 Number of revolutions: 18000	Final grade: 2

\*) Not covered by the accreditation reg. no. 2

---